## Comment on "Multiferroicity Induced by Dislocated Spin-Density Waves"

A recent Letter by Betouras *et al.* [1] (BGB) proposed a phenomenological magnetoelectric (ME) interaction to explain the spontaneous polarization  $\mathbf{P}$  in a class of materials of which YMn<sub>2</sub>O<sub>5</sub> (YMO) was taken to be the best exemplar. They claimed 1) its behavior agreed perfectly with their theory and 2) previous theories failed in this regard. Here I show that these claims are incorrect and that their interaction is unimportant in most systems.

Figure 1 shows **P** measured by Kagomiya *et al.* [3] compared to the microscopic theory of Chapon *et al.* [2]. The ME interaction proposed by BGB gives **P**=0 in the low-temperature (T < 20K) incommensurate (IC) phase and, as I will discuss, nearly zero in the high-temperature (T > 20K) commensurate (CM) phase. Below I show that the Landau approach [5] fits the data qualitatively.

Fig. 1. (Based on Ref. 2.)  $\mathbf{P}$  vs T for YMO. Filled circles: theory of Ref. 2. Thin line: data of Kagomiya *et al.*[3] The dashed line indicates the IC-CM phase boundary.



The results of Ref. 1 follow from a gradient expansion of the free energy to mimic the variation of magnetization on an atomic length scale. However, the most successful long-wavelength treatment of antiferromagnets [4] utilizes the symmetry of both the staggered and direct magnetization. The generalization to the multisublattice case of YMO is to consider all the symmetry elements of the unit cell as done in Refs. 5-9. There one introduced order parameters  $\sigma_n$  of known symmetry to describe the magnetism of the unit cell and for YMO the trilinear ME coupling is [9]  $V = aP[|\sigma_1|^2 - |\sigma_2|^2]$ , which gives  $P = \text{const} \times [|\sigma_2|^2 - |\sigma_1|^2]$ . I will call this the "standard" model and it was used [9] to successfully interpret the polarization of the CM phase of YMO. I show here that this formulation can also explain the smaller nonzero polarization in the IC phase which contradicts Ref. 1. For this purpose we need to extract the order parameters for YMO since they were not given in Ref. 2. The symmetry of the spin pattern shown in their Fig. 2a [10] for the CM phase indicates that the order parameter called  $\sigma_1$  in Ref. 9 is zero. [9] To normalize the results, I define  $\sigma_2 = 1$ . Although the size of the moments does not change much at the CM-IC transition, the orientations of the moments do change and this change induces a significant redistribution of the order parameters. To see this consider the relation in their Fig. 2a between the  $Mn^{3+}$  spins at (0.09,-0.15,0.5) and at (0.41,0.35,0.5). In the CM phase their *x*-components are the same but their *y*-components change sign. In the IC phase both *x* and *y*- components change sign. This change in spin orientation induces significant changes in the order parameters. I found the order parameters of the T = 1.9K structure to be such that  $|\sigma_2|^2 - |\sigma_1|^2$  lies between -0.25 and +0.25. Even with this uncertainty it is clear that the change in the magnetic structure can explain the precipitate decrease in P at the CM to IC phase boundary.

Since the microscopic model of Ref. 2 is so satisfactory, one can ask whether it is consistent with either or both of the competing phenomenological theories. To answer this question I write the ME interaction of BGB in the language of order parameters effectively as

$$V = \operatorname{const} \times P\sigma(q)^n \delta(n\mathbf{q}, \mathbf{G}) + \operatorname{c. c.}, \quad (1)$$

where the  $\delta$  function conserves momentum to within a nonzero reciprocal lattice vector  $\mathbf{G}$  (so that  $n\mathbf{q} = \mathbf{G}$ ). For YMO, n = 4 in Eq. (1), since one of the magnetic unit cell axes is four times that of the paramagnetic unit cell. The theory of Chapon *et al.* is quadratic in the spin operators. It can not give rise to  $4\mathbf{q} = \mathbf{G}$ , because this would require either a four-spin ME interaction or treating the standard two-spin ME interaction in secondorder perturbation theory. However, this latter possibility is quite remote because the ME interaction is already quite weak in systems where the ME interaction acts in first order perturbation theory. So the Chapon *et al.* model, which fits the data nicely, is not a microscopic representation of the ME interaction of BGB. But since the model of Ref. 2 gives the polarization as a quadratic form in the spin operators, it is the microscopic analog of the "standard" model, which I therefore claim does represent the data well. Moreover, rather than happening in a wide class of materials, the BGB interaction might be important, but only when the magnetic unit cell involves doubling of the paramagnetic unit cell.

In summary: the existing "standard" model explains the data of Fig. 1 qualitatively, whereas that of BGB does not and is unlikely to be important for most systems.

I thank A. P. Ramirez and T. Yildirim for suggestions. A. B. Harris

Department of Physics and Astronomy University of Pennsylvania Philadelphia, PA 19104

- <sup>1</sup> J. J. Betouras, G. Giovannetti, and J. van den Brink, Phys. Rev. Lett. **98**, 257602 (2007).
- <sup>2</sup> L. C. Chapon *et al.*, Phys. Rev. Lett. **96**, 097601 (2006).
- <sup>3</sup> I. Kagomiya *et al.*, Ferroelectrics **286**, 167 (2003).
- <sup>4</sup> B. I. Halperin and P. C. Hohenberg, Phys. Rev. **188**, 898 (1969).
- <sup>5</sup> G. Lawes *et al.*, Phys. Rev. Lett. **95**, 087205 (2005).
- <sup>6</sup> M. Kenzelmann *et al.*, Phys. Rev. Lett. **95**, 087206 (2005).
- <sup>7</sup> M. Kenzelmann *et al.*, Phys. Rev. B **74**, 014429 (2006).
- <sup>8</sup> A. B. Harris, J. Appl. Phys. **99**, 08E303 (2006).
- <sup>9</sup> A. B. Harris, cond-mat/0610241.
- $^{10}$  The top (bottom) panel should be labeled 24.7K (1.9K).