Theoretical derivation of the bi- and tri-molecular trion formation coefficients

J. Berney,^{1,2} M.T. Portella-Oberli,¹ and B. Deveaud-Plédran¹

¹Institut de Photonique et Electronique Quantiques,

Ecole Polytechnique Fédérale de Lausanne (EPFL) CH1015 Lausanne, Switzerland

²Attolight Sàrl, Chemin de la Raye 13, CH1024 Ecublens, Switzerland

(Dated: October 29, 2018)

A theoretical investigation of the trion formation process from free carriers in a single GaAs/ $Al_{1-x}Ga_xAs$ quantum well is presented. The mechanism for the formation process is provided by the interaction of the electrons and holes with phonons. The contributions from both the acoustic and optical phonons are considered. The dependence of both bi-molecular and tri-molecular formation rates on temperature is calculated. We demonstrate that they are equivalent for negatively and positively charged excitons.

PACS numbers: 71.35.Cc,71.35.Ee,73.21.Fg,78.47.+p,78.67.De

I. INTRODUCTION

In semiconductor wells, the photoluminescence spectrum following the generation of electron hole plasma is dominated by an exciton $line^{1,2,3,4,5,6}$. The formation of excitons in quantum wells has been extensively investigated both experimentally^{4,5,6,7,8,9} and theoretically 10,11,12 . Recently, it was experimentally showed that the exciton formation is strongly density and temperature dependent; it is a bimolecular process in which an electron and a hole are bound by Coulomb interaction with the emission of the appropriate $phonon^8$. This experimental result unambiguously confirmed the theoretical prediction for luminescence spectrum is modified: a charged exciton resonance appears below that of the exciton.

In a previous publication¹³, we showed experimentally that the dynamics of exciton, trion and electron-hole plasma can be ruled by a simple rate equation model, in which we account for bimolecular formation of excitons from an electron-hole plasma, bimolecular formation of trions from excitons and free carriers and trimolecular formation from free carriers. Using only two fit parameters, we were able to extract experimentally the dependence of both bi-molecular and tri-molecular formation coefficients on temperature.

In this paper, we propose a theoretical derivation of these coefficients. We consider formation channels through which the formation channel and show that they correspond to experimental calculations.

In Sec. I, we first reproduce the results of Piermarocchi et al.¹² on exciton formation. We then extend the formalism to the case of charged excitons; in Sec. II, we calculate the bi-molecular formation and in Sec. III the tri-molecular formation. In Sec. IV, we show how these formation rates can be used to calculate formation dynamics at thermodynamical equilibrium.

II. BIMOLECULAR FORMATION OF EXCITONS

The dynamics of the exciton formation is considered in the framework of the Boltzmann equation for a system containing free electrons, free holes, and excitons. The residual Coulomb interaction between the free carriers is neglected, which is justified in the range of temperatures and densities considered¹³. In this work we focus on the exciton formation mechanism and do not discuss the relaxation of the three species within their respective bands, the electron-hole scattering, and radiative recombination. We denote the occupation numbers for electrons, holes, and excitons by $f_e(\mathbf{k}_e)$, $f_h(\mathbf{k}_h)$, and $f_X(\mathbf{k}_X)$, respectively, where $\mathbf{k}_e, \mathbf{k}_h$, and \mathbf{k}_X are the inplane momenta for electrons, holes, and excitons. For the bimolecular formation, following Piermarocchi et al.¹², the scattering terms in the Boltzmann equation process reads

$$\left(\frac{\mathrm{d}f_{e}(\boldsymbol{k}_{e})}{\mathrm{d}t}\right)_{form} = -\sum_{\boldsymbol{k}_{X},\boldsymbol{k}_{h}} w_{\boldsymbol{k}_{e},\boldsymbol{k}_{h}\to\boldsymbol{k}_{X}} f_{h}(\boldsymbol{k}_{h}) f_{e}(\boldsymbol{k}_{e}),$$
(1)

where $w_{\mathbf{k}_e,\mathbf{k}_h\to\mathbf{k}_X}$ represents the probability per unit time for a free electron and a free hole to bind together and form an exciton. Free carriers thermalize very quickly in comparison to the exciton formation time, notably through fast carrier-carrier scattering¹⁴. It is thus assumed that during the evolution of the system, the free electrons and holes are thermalized at the same temperature T_c . In the scattering term of Eq. (1), we use for $f_e(k_e)$, and $f_h(k_h)$ equilibrium Boltzmann distribution function at T_c . Consequently, by summing Eq. (1) over \mathbf{k}_e , we obtain an adiabatic equation for the evolution of the electronic density $n_e = \frac{1}{S} \sum_{\mathbf{k}_e} f_e(\mathbf{k}_e)$

$$\frac{\mathrm{d}n_{e}}{\mathrm{d}t} = -\sum_{\boldsymbol{k}_{\boldsymbol{X}}} F(\boldsymbol{k}_{\boldsymbol{X}}) n_{e} n_{h} \equiv -C n_{e} n_{h}.$$
(2)

The coefficient C is the bimolecular formation coefficient, which depends on both T_c and the lattice temperature T_l through the term

$$F(\mathbf{k}_{\mathbf{X}}) = \left(\frac{2\pi\hbar^2}{k_B T_c}\right)^2 \frac{1}{m_e m_h S} \times \sum_{\mathbf{k}_e, \mathbf{k}_h} w_{\mathbf{k}_e, \mathbf{k}_h \to \mathbf{k}_{\mathbf{X}}} e^{-(E_e(\mathbf{k}_e) + E_h(\mathbf{k}_h))/k_B T_c}, \quad (3)$$

where S denotes the QW surface area.

Free carriers are coupled to the exciton by a continuum of phonon states (q, q_z) through a carrier-phonon interaction Hamiltonian $\mathcal{H}_{e/h-ph}$. A phonon can be emitted (+) or absorbed (-) in the formation process of the exciton. We calculate both case separatly using the Fermi's golden rule

$$w_{\boldsymbol{k}_{e},\boldsymbol{k}_{h}\rightarrow\boldsymbol{k}_{X}}^{\pm} = \frac{2\pi}{\hbar} \sum_{\boldsymbol{q},q_{z}} \left| \langle \boldsymbol{k}_{X} | \otimes \langle n_{\boldsymbol{q},q_{z}} \pm 1 | \mathcal{H}_{e/h-ph} | n_{\boldsymbol{q},q_{z}} \rangle \otimes | \boldsymbol{k}_{e} \rangle \otimes | \boldsymbol{k}_{h} \rangle \right|^{2} \times \delta \left[E_{e}(\boldsymbol{k}_{e}) + E_{h}(\boldsymbol{k}_{h}) - E_{X}(\boldsymbol{k}_{X}) \mp \hbar \omega_{ph}(\boldsymbol{q},q_{z}) \right], \quad (4)$$

with $E_e(\mathbf{k}_e)$, $E_h(\mathbf{k}_h)$ and $E_X(\mathbf{k}_X)$ the energy dispertion of the electrons, holes and excitons respectively, and $\hbar\omega_{ph}(\mathbf{q}, q_z)$ the energy of the emitted (absorbed) phonon. We first build the bound and unbound electron-hole pair states $|\mathbf{k}_X\rangle$ and $|\mathbf{k}_e\rangle \otimes |\mathbf{k}_h\rangle$.

A. Bound and unbound exciton states

Let $(\mathbf{r}_{e\parallel}, z_e)$ and $(\mathbf{r}_{h\parallel}, z_h)$ be the electron and hole position vectors respectively and $\Phi^X[(\mathbf{r}_{e\parallel}, z_e), (\mathbf{r}_{h\parallel}, z_h)]$ the exciton wavefunction, where we have separated the coordinates in the QW plane (x-y) from the perpendicular coordinates (z). Denoting the electron (hole) in-plane momenta \mathbf{k}_e (\mathbf{k}_h), we write the in-plane Fourier transform of this function

$$\Phi_{\boldsymbol{k}_{e},\boldsymbol{k}_{h}}^{X}(z_{e},z_{h}) = \frac{1}{S} \int \mathrm{d} r_{e\parallel} \mathrm{d} r_{h\parallel} \Phi^{X}[(\boldsymbol{r}_{e\parallel},z_{e}),(\boldsymbol{r}_{h\parallel},z_{h})] \times e^{-i(\boldsymbol{k}_{e}\cdot\boldsymbol{r}_{e\parallel}+\boldsymbol{k}_{h}\cdot\boldsymbol{r}_{h\parallel})},$$
(5)

where S denotes the QW surface area. Transforming to center-of-mass (CM) and relative coordinates in the QW plane — $\mathbf{R}_{\parallel} = \alpha_X \mathbf{r}_{e\parallel} + \beta_X \mathbf{r}_{h\parallel}$, $\mathbf{r}_{\parallel} = \mathbf{r}_{e\parallel} - \mathbf{r}_{h\parallel}$, where $\alpha_X = m_e/M_X$, $\beta_X = m_h/M_X$ and m_e , m_h , M_X are the electron, hole and exciton in-plane effective mass we can apply Bloch's theorem and decompose the exciton wavefunction into a free motion part $e^{i\mathbf{k}_X \cdot \mathbf{R}_{\parallel}}$ related to the exciton in-plane momentum \mathbf{k}_X and an envelope function. To facilitate the calculation, we use an envelope function separable in z and r_{\parallel} , although it is strictly justifiable only for narrow well structures,

$$\phi^X(r_{\parallel}, z_e, z_h) = \chi_e(z_e)\chi_h(z_h)\varphi^{\lambda_X}(r_{\parallel}).$$
(6)

The confinement functions $\chi_e(z_e)$ ($\chi_h(z_h)$) is taken to be the wavefunction of an electron (hole) in the ground state of a finite square quantum well¹⁵

$$\chi_{\alpha}(z_{\alpha}) = \begin{cases} A_{\alpha} \cos\left(k_{z}^{w(\alpha)} z_{\alpha}\right) & \text{for } |z_{\alpha}| < \frac{L_{z}}{2} \\ B_{\alpha} \exp\left(-k_{z}^{b(\alpha)}(|z_{\alpha}| - L_{z}/2)\right) & \text{for } |z_{\alpha}| > \frac{L_{z}}{2} \\ \end{cases}$$
(7)

with $\alpha=e,h$ and we use the simplest electron orbital function

$$\varphi^{\lambda_X}(r_{\parallel}) = \sqrt{\frac{2}{\pi \lambda_X^2}} e^{-r_{\parallel}/\lambda_X}, \qquad (8)$$

whose in-plane Fourier transform is given by

$$\varphi_{\boldsymbol{k}}^{\lambda_X} = \sqrt{\frac{8\pi\lambda_X^2}{S}} \left[1 + (\lambda_X k)^2\right]^{-3/2}.$$
 (9)

The variational parameter λ_X is associated with the Bohr radius of the exciton in the QW. Eq. (5) can be rewritten as

$$\Phi_{\boldsymbol{k}_{e},\boldsymbol{k}_{h}}^{X}(z_{e},z_{h}) = \frac{1}{S} \int \mathrm{d} R_{\parallel} \mathrm{d} r_{\parallel} \phi^{X}(r_{\parallel},z_{e},z_{h}) \\ \times e^{i\boldsymbol{k}_{X}\cdot\boldsymbol{R}_{\parallel}} e^{-i[\boldsymbol{R}_{\parallel}\cdot(\boldsymbol{k}_{e}+\boldsymbol{k}_{h})+\boldsymbol{r}_{\parallel}\cdot(\beta_{X}\boldsymbol{k}_{e}-\alpha_{X}\boldsymbol{k}_{h})]} \\ = \delta_{\boldsymbol{k}_{X}-\boldsymbol{k}_{e}-\boldsymbol{k}_{h}} \phi_{\boldsymbol{k}_{e}-\alpha_{X}\boldsymbol{k}_{X}}^{X}(z_{e},z_{h}), \qquad (10)$$

where $\phi_{\mathbf{k}}^{X}(z_{e}, z_{h}) = \chi_{e}(z_{e})\chi_{h}(z_{h})\varphi_{\mathbf{k}}^{\lambda_{X}}$ is the in-plane Fourier transform of the exciton envelope function. We can now construct the state of a single exciton with an in-plane momentum \mathbf{k}_{X} in the Fermionic Hilbert space of electron-hole pairs. It is the superposition of wavefunctions (10) with all electron momenta \mathbf{k}_{e} and all electron z_{e} and hole z_{h} coordinates, given by

$$|\mathbf{k}_{X}\rangle = \sum_{\mathbf{k}_{e}} \int \mathrm{d}z_{e} \,\mathrm{d}z_{h} \,\phi_{\alpha_{X}\mathbf{k}_{X}+\mathbf{k}_{e}}^{X*}(z_{e}, z_{h})$$
$$\times \hat{c}_{-\mathbf{k}_{e}, z_{e}}^{\dagger} \hat{d}_{\mathbf{k}_{X}+\mathbf{k}_{e}, z_{h}}^{\dagger} |0\rangle, \qquad (11)$$

where $\hat{c}^{\dagger}_{\boldsymbol{k}_{X},z_{e}}(\hat{d}^{\dagger}_{\boldsymbol{k}_{X},z_{h}})$ is the electron (hole) creation operator with in-plane momentum \boldsymbol{k}_{X} and $z_{e}(z_{h})$ coordinate.

Similarly, we choose plane waves for the free carriers. Thus the in-plane Fourier transform $\psi^{\alpha}_{\pmb{k}}(z)$ of the carrier wavefunction takes the simple form

$$\psi_{\boldsymbol{k}}^{\alpha}(z) = \chi_{\alpha}(z), \quad \alpha = e, h.$$
(12)

The unbound electron-hole pair then reads

$$|\boldsymbol{k}_{e},\boldsymbol{k}_{h}\rangle = \int \mathrm{d}z_{e} \,\mathrm{d}\,z_{h}\,\psi_{\boldsymbol{k}_{e}}^{e*}(z_{e})\,\psi_{\boldsymbol{k}_{h}}^{h*}(z_{h})\hat{c}_{\boldsymbol{k}_{e},z_{e}}^{\dagger}\hat{d}_{\boldsymbol{k}_{h},z_{h}}^{\dagger}\left|0\right\rangle.$$
(13)

B. Carrier-phonon interaction Hamiltonian.

We write the interaction Hamiltonian for a coupled electron-phonon system in the notation of the second quantization 16

$$\mathcal{H}_{\alpha-ph} = \sum_{\boldsymbol{q},q_z} V^{\alpha}_{\boldsymbol{q},q_z} \left(\hat{a}_{\boldsymbol{q},q_z} + \hat{a}^{\dagger}_{-\boldsymbol{q},-q_z} \right) \hat{\varrho}_{\alpha}(\boldsymbol{q},q_z) \quad (14)$$

where $\hat{a}_{q,q_z}^{\dagger}$ is the phonon creation operator. The electron density operator $\hat{\varrho}_{\alpha}(\boldsymbol{r}_{\parallel},z)$ and its counterpart in Fourier space $\hat{\rho}_{\alpha}(\boldsymbol{q}, q_z)$ are expressed on the basis $\left\{\phi_{\boldsymbol{k}}^{\sigma}(\boldsymbol{r}_{\parallel}, z, s) = e^{i\boldsymbol{k}\cdot\boldsymbol{r}_{\parallel}}\delta(z)\zeta_{\sigma}(s)\right\}$

$$\hat{\varrho}_{e}^{\sigma}(\boldsymbol{r}_{\parallel},z) = \sum_{\boldsymbol{k},\boldsymbol{k}'} \hat{c}_{\boldsymbol{k},z}^{\sigma\dagger} \hat{c}_{\boldsymbol{k}',z}^{\sigma} e^{-i(\boldsymbol{k}-\boldsymbol{k}')\cdot\boldsymbol{r}_{\parallel}}, \qquad (15)$$

$$\hat{\varrho}_{e}^{\sigma}(\boldsymbol{q}, q_{z}) = \sum_{\boldsymbol{k}} \int \mathrm{d}z \ e^{-iq_{z}z} \hat{c}_{\boldsymbol{k}+\boldsymbol{q},z}^{\sigma\dagger} \hat{c}_{\boldsymbol{k},z}^{\sigma}, \tag{16}$$

$$\hat{\varrho}_{h}^{\sigma}(\boldsymbol{r}_{\parallel},z) = -\sum_{\boldsymbol{k},\boldsymbol{k}'} \hat{d}_{\boldsymbol{k},z}^{\sigma\dagger} \hat{d}_{\boldsymbol{k}',z}^{\sigma} e^{-i(\boldsymbol{k}-\boldsymbol{k}')\cdot\boldsymbol{r}_{\parallel}}, \qquad (17)$$

$$\hat{\varrho}_{h}^{\sigma}(\boldsymbol{q}, q_{z}) = -\sum_{\boldsymbol{k}} \int \mathrm{d}z \ e^{-iq_{z}z} \hat{d}_{\boldsymbol{k}+\boldsymbol{q},z}^{\sigma\dagger} \hat{d}_{\boldsymbol{k},z}^{\sigma}.$$
 (18)

Spin states $\zeta_{\sigma}(s) = \langle \sigma | s \rangle$ have been intruduced for their will be necessary when we treat the trion formation.

Only longitudinal acoustical (LA) and longitudinal optical phonons (LO) couple significantly to careers. We express the coupling vertex functions $V^{\alpha}_{\boldsymbol{q},q_z}$ for both coupling

$$V_{\boldsymbol{q},q_z}^{\alpha\,(LA)} = i a_\alpha \sqrt{\frac{\hbar(|\boldsymbol{q}|^2 + q_z^2)}{2\rho_0 V \omega_{\boldsymbol{q},q_z}}},\tag{19}$$

$$V_{\boldsymbol{q},q_z}^{\alpha\,(LO)} = \sqrt{\frac{2\pi\hbar\omega_{\boldsymbol{q},q_z}e^2}{(|\boldsymbol{q}|^2 + q_z^2)V} \left(\frac{1}{\epsilon_0} - \frac{1}{\epsilon_\infty}\right)},\qquad(20)$$

where ϵ_0 is the static dielectric constant and ϵ_{∞} is the high frequency dielectric constant. We use the notation a_{α} for the deformation-potential constant (assumed to be associated with a non-degenerate conduction or valence band), ρ_0 for the density of the crystal, e for the charge of the electron and V for the volume of the sample. We follow Einstein interpolation scheme, so that the dispersion is merely $\omega_{q}^{LA} = v_s \sqrt{q^2 + q_z^2}$ for LA phonons and $\omega_{q}^{LO} = \omega_{LO}$ for LO phonons, v_s standing for the Debye sound velocity and ω_{LO} for the reststrahl frequency.

C. Matrix element calculation.

The matrix elements in Eq. (4) are calculated, making use of Eq. (11), (13) and (14)

$$\begin{split} \langle \boldsymbol{k}_{X}, \boldsymbol{n}_{\boldsymbol{q},q_{z}} \pm 1 | \mathcal{H}_{e-ph} + \mathcal{H}_{h-ph} | \boldsymbol{k}_{e}, \boldsymbol{k}_{h}, \boldsymbol{n}_{\boldsymbol{q},q_{z}} \rangle \\ &= \sum_{\tilde{\boldsymbol{q}},\tilde{q}_{z}} \sum_{\boldsymbol{k},\boldsymbol{k}_{e}^{\prime}} \int \mathrm{d}z_{e} \, \mathrm{d}z_{h} \, \mathrm{d}z_{e}^{\prime} \, \mathrm{d}z_{h}^{\prime} \, \mathrm{d}z \, \varphi_{\alpha \boldsymbol{k}_{X} + \boldsymbol{k}_{e}^{\prime}}^{X} \langle \boldsymbol{n}_{\boldsymbol{q},q_{z}} \pm 1 | \hat{a}_{\pm \tilde{q},\tilde{q}_{z}} \hat{a}_{-\tilde{\boldsymbol{q}},-\tilde{q}_{z}}^{\dagger} | \boldsymbol{n}_{\boldsymbol{q},q_{z}} \rangle \chi_{e}^{*}(z_{e}) \chi_{e}(z_{e}^{\prime}) \chi_{h}^{*}(z_{h}) \chi_{h}(z_{h}^{\prime}) e^{-i\tilde{q}_{z}z} \\ &\times \Big\{ V_{\tilde{\boldsymbol{q}},\tilde{q}_{z}}^{e} \langle 0 | \hat{c}_{-\boldsymbol{k}_{e}^{\prime},z_{e}^{\prime}} \hat{c}_{\boldsymbol{k}+\tilde{\boldsymbol{q}},z}^{\dagger} \hat{c}_{\boldsymbol{k},z} \hat{c}_{\boldsymbol{k}_{e},z_{e}}^{\dagger} | 0 \rangle \langle 0 | \hat{d}_{\boldsymbol{k}_{X} + \boldsymbol{k}_{e}^{\prime},z_{h}^{\prime}} \hat{d}_{\boldsymbol{k}_{h},z_{h}}^{\dagger} | 0 \rangle - V_{\tilde{\boldsymbol{q}},\tilde{q}_{z}}^{h} \langle 0 | \hat{c}_{-\boldsymbol{k}_{e}^{\prime},z_{e}^{\prime}} \hat{c}_{\boldsymbol{k}_{e},z_{e}}^{\dagger} | 0 \rangle \langle 0 | \hat{d}_{\boldsymbol{k}_{X} + \boldsymbol{k}_{e}^{\prime},z_{h}^{\prime}} \hat{d}_{\boldsymbol{k}_{h},z_{h}}^{\dagger} | 0 \rangle - V_{\tilde{\boldsymbol{q}},\tilde{q}_{z}}^{h} \langle 0 | \hat{c}_{-\boldsymbol{k}_{e}^{\prime},z_{e}^{\prime}} \hat{c}_{\boldsymbol{k}_{e},z_{e}}^{\dagger} | 0 \rangle \langle 0 | \hat{d}_{\boldsymbol{k}_{X} + \boldsymbol{k}_{e}^{\prime},z_{h}^{\prime}} \hat{d}_{\boldsymbol{k}_{h},z_{h}}^{\dagger} | 0 \rangle \Big\}. \end{split}$$
Applying operators on the ground state

$$\langle 0|\hat{c}_{-\mathbf{k}'_{e},z'_{e}}\hat{c}^{\dagger}_{\mathbf{k}+\tilde{\mathbf{q}},z}\hat{c}_{\mathbf{k},z}\hat{c}^{\dagger}_{\mathbf{k}_{e},z_{e}}|0\rangle = \delta_{-\mathbf{k}'_{e},\mathbf{k}+\tilde{\mathbf{q}}}\,\delta(z-z'_{e})\,\delta_{\mathbf{k},\mathbf{k}_{e}}\,\delta(z-z_{e}), \qquad \langle 0|\hat{c}_{-\mathbf{k}'_{e},z'_{e}}\hat{c}^{\dagger}_{\mathbf{k}_{e},z_{e}}|0\rangle = \delta_{\mathbf{k}_{e},-\mathbf{k}'_{e}}\,\delta(z_{e}-z'_{e}), \\ \langle 0|\hat{d}_{\mathbf{k}_{X}+\mathbf{k}'_{e},z'_{h}}\hat{d}^{\dagger}_{\mathbf{k}+\tilde{\mathbf{q}},z}\hat{d}_{\mathbf{k},z}\hat{d}^{\dagger}_{\mathbf{k}_{h},z_{h}}|0\rangle = \delta_{\mathbf{k}_{X}+\mathbf{k}'_{e},\mathbf{k}+\tilde{\mathbf{q}}}\,\delta(z-z'_{h})\,\delta_{\mathbf{k},\mathbf{k}_{h}}\,\delta(z-z_{h}), \qquad \langle 0|\hat{d}_{\mathbf{k}_{X}+\mathbf{k}'_{e},z'_{h}}\hat{d}^{\dagger}_{\mathbf{k}_{h},z_{h}}|0\rangle = \delta_{\mathbf{k}_{h},\mathbf{k}_{X}+\mathbf{k}'_{e}}\,\delta(z_{h}-z'_{h}), \\ \langle n_{\mathbf{q},q_{z}}\pm1|\hat{a}_{\tilde{\mathbf{q}},\tilde{q}_{z}}+\hat{a}^{\dagger}_{-\tilde{\mathbf{q}},-\tilde{q}_{z}}|n_{\mathbf{q},q_{z}}\rangle = \sqrt{n_{\mathbf{q},q_{z}}+\frac{1}{2}\pm\frac{1}{2}}\,\delta_{\mp\tilde{\mathbf{q}},\mathbf{q}}\,\delta_{\mp\tilde{q}_{z},q_{z}},$$

we obtain

/ 7

$$\langle \boldsymbol{k}_{X}, \boldsymbol{n}_{\boldsymbol{q},q_{z}} \pm 1 | \mathcal{H}_{\text{e-ph}} + \mathcal{H}_{\text{h-ph}} | \boldsymbol{k}_{e}, \boldsymbol{k}_{h}, \boldsymbol{n}_{\boldsymbol{q},q_{z}} \rangle$$

$$= \sqrt{n_{\boldsymbol{q},q_{z}} + \frac{1}{2} \pm \frac{1}{2}} \, \delta_{\pm \boldsymbol{q},\boldsymbol{k}_{e} + \boldsymbol{k}_{h} - \boldsymbol{k}_{X}} \left\{ V_{\boldsymbol{q},q_{z}}^{e} \varphi_{-\beta_{X}\boldsymbol{k}_{X} + \boldsymbol{k}_{h}}^{X} I_{e}(q_{z}) - V_{\boldsymbol{q},q_{z}}^{h} \varphi_{\alpha_{X}\boldsymbol{k}_{X} - \boldsymbol{k}_{e}}^{X} I_{h}(q_{z}) \right\}, \quad (21)$$

where the integrals, in the orthogonal direction are given by

$$I_{\alpha}(q_z) = \int \mathrm{d}z_{\alpha} |\chi_{\alpha}(z_{\alpha})|^2 e^{iq_z z_{\alpha}}, \qquad \alpha = \{e, h\}.$$
(22)

Finally, if we choose the bound and unbound electron-hole pairs dispersion to be parabolic, the probability transition (4) reads

$$w_{\boldsymbol{k}_{e},\boldsymbol{k}_{h}\rightarrow\boldsymbol{k}_{X}}^{\pm} = \frac{2\pi}{\hbar} \sum_{\boldsymbol{q},q_{z}} (n_{\boldsymbol{q},q_{z}} + \frac{1}{2} \pm \frac{1}{2}) \left| V_{\boldsymbol{q},q_{z}}^{e} \varphi_{\beta_{X}\boldsymbol{k}_{X}-\boldsymbol{k}_{h}}^{X} I_{e}(q_{z}) - V_{\boldsymbol{q},q_{z}}^{h} \varphi_{\alpha_{X}\boldsymbol{k}_{X}-\boldsymbol{k}_{e}}^{X} I_{h}(q_{z}) \right|^{2} \\ \times \delta \left[\frac{\hbar^{2}k_{e}^{2}}{2m_{e}} + \frac{\hbar^{2}k_{h}^{2}}{2m_{h}} + E_{b} - \frac{\hbar^{2}k_{X}^{2}}{2M} \mp \hbar\omega_{ph}(\boldsymbol{q},q_{z}) \right] \delta_{\pm\boldsymbol{q},\boldsymbol{k}_{e}+\boldsymbol{k}_{h}-\boldsymbol{k}_{X}}.$$
(23)

D. LA phonons assisted formation

and reexpressing the Dirac distribution as

Considering that the sample volume $V = L_z S$ is macroscopic the sum over the orthogonal phonon wavevectors may be replaced by the integral

$$\sum_{q_z} \longleftrightarrow \quad \left(\frac{L_z}{2\pi}\right) \int \mathrm{d}q \,_z \tag{24}$$

$$\delta \left[\frac{\hbar^2 k_e^2}{2m_e} + \frac{\hbar^2 k_h^2}{2m_h} + E_b - \frac{\hbar^2 k_X^2}{2M} \mp \hbar v_s \sqrt{q^2 + q_z^2} \right] \\ = \frac{\sqrt{q^2 + q_z^2}}{|\hbar v_s q_z|} \left\{ \delta \left[q_z - q_z^{(0)}(\boldsymbol{k}_e, \boldsymbol{k}_h, \boldsymbol{k}_X) \right] + \delta \left[q_z + q_z^{(0)}(\boldsymbol{k}_e, \boldsymbol{k}_h, \boldsymbol{k}_X) \right] \right\} \; \theta \left[\pm \left(\frac{\hbar^2 k_e^2}{2m_e} + \frac{\hbar^2 k_h^2}{2m_h} + E_b - \frac{\hbar^2 k_X^2}{2M} \right) \right], \quad (25)$$

with

$$q_z^{(0)}(\mathbf{k}_e, \mathbf{k}_h, \mathbf{k}_X) = \sqrt{\frac{1}{\hbar^2 v_s^2} \left(\frac{\hbar^2 k_e^2}{2m_e} + \frac{\hbar^2 k_h^2}{2m_h} + E_b - \frac{\hbar^2 k_X^2}{2M}\right)^2 - q^2},$$
(26)

makes the integration (24) trivial for LA phonons:

 $\times \left| a_e \varphi^X_{\beta_X \boldsymbol{k}_X - \boldsymbol{k}_h} I_e(q_z^{(0)}) - a_h \varphi^X_{\alpha_X \boldsymbol{k}_X - \boldsymbol{k}_e} I_h(q_z^{(0)}) \right|^2$

 $\times \left\{ \left(n_{q,q_{z}^{(0)}} + 1 \right) \; \theta \left(\frac{\hbar^{2}k_{e}^{2}}{2m_{e}} + \frac{\hbar^{2}k_{h}^{2}}{2m_{h}} + E_{b} - \frac{\hbar^{2}k_{X}^{2}}{2M} \right) \right.$

 $+ n_{\mathbf{q},q_{z}^{(0)}} \theta \left(-\frac{\hbar^{2}k_{e}^{2}}{2m_{e}} - \frac{\hbar^{2}k_{h}^{2}}{2m_{h}} - E_{b} + \frac{\hbar^{2}k_{X}^{2}}{2M} \right) \right\}.$ (27)

This expression already includes the sum over absorbed and emitted phonon contributions. The phonon in-plane

momentum needs to be substituted by $q = k_e + k_h - k_X$.

 $w_{\mathbf{k}_e,\mathbf{k}_h\to\mathbf{k}_X} = \frac{4\pi}{\hbar} \frac{L_z}{2\pi} \frac{\hbar}{2\rho V v_s} \frac{q^2 + q_z^{(0)^2}}{|\hbar v_s q_z^{(0)}|}$

E. LO phonons assisted formation

In the case of interaction with LO phonons, Eq. 23 becomes

$$w_{\boldsymbol{k}_{e},\boldsymbol{k}_{h}\rightarrow\boldsymbol{k}_{X}} = \sum_{q_{z}} \frac{2\pi}{\hbar} \frac{\hbar\omega_{LO}e^{2}(1/\epsilon_{\infty}-1/\epsilon_{0})}{V(q^{2}+q_{z}^{2})} n_{\boldsymbol{q},q_{z}}$$

$$\times \left|\varphi_{\beta_{X}\boldsymbol{k}_{X}-\boldsymbol{k}_{h}}^{X}I_{e}(q_{z})-\varphi_{\alpha_{X}\boldsymbol{k}_{X}-\boldsymbol{k}_{e}}^{X}I_{h}(q_{z})\right|^{2}$$

$$\times \delta \left[\frac{\hbar^{2}k_{e}^{2}}{2m_{e}}+\frac{\hbar^{2}k_{h}^{2}}{2m_{h}}+E_{b}-\frac{\hbar^{2}k_{X}^{2}}{2M}+\hbar\omega_{LO}\right], \quad (28)$$

where we dropped the phonon absorption part, which is negligible up to room temperature. For the calculation of the exciton formation coefficient C, it is convenient to rewrite the Dirac distribution as

$$\delta \left[\frac{\hbar^2 k_e^2}{2m_e} + \frac{\hbar^2 k_h^2}{2m_h} + E_b - \frac{\hbar^2 k_X^2}{2M} + \hbar\omega_{LO} \right]$$

= $\frac{M_X}{\hbar} \left\{ \delta \left[k_X - k_X^{(0)}(\boldsymbol{k}_e, \boldsymbol{k}_h)) \right] + \delta \left[k_X + k_X^{(0)}(\boldsymbol{k}_e, \boldsymbol{k}_h) \right] \right\},$ (29)



FIG. 1: The exciton formation coefficient C as a function of the carrier temperature T_c , at a fixed lattice temperature $T_l = 10$ K. Other parameters are given in the text.

with

$$k_X^{(0)}(\boldsymbol{k}_e, \boldsymbol{k}_h) = \sqrt{\frac{2M_X}{\hbar^2} \left(\frac{\hbar^2 k_e^2}{2m_e} + \frac{\hbar^2 k_h^2}{2m_h} + E_b - \hbar\omega_{LO}\right)},$$
(30)

F. Numerical Results.

If we change all the sum in Eq. 2, 3, 27 and 28 into integrals, the bimolecular formation coefficient C can be numerically calculated by Monte Carlo integration. In Fig. 1, we report C as a function of $1/T_c$ for a fixed lattice temperature $T_l = 5$ K, for a GaAs QW of 80 Å. The two contributions from the acoustic and optical phonons are shown separately. The acoustical phonon dominates for temperatures smaller than 40 K and does not depend on T_l . We see that these results perfectly match those published by Piermarocchi et al.¹². We show in Table I the numerical value of the different parameters entering in the calculation.

III. BIMOLECULAR FORMATION OF TRIONS

We now extend our formalism to the derivation of the bimolecular formation of trions. We restrict ourselves to negatively charged excitons and will give at the end of this work some indication on how to retrieve their positive counterpart.

We write the scattering term in the Boltzmann equation process for the bimolecular formation of trions:

$$\left(\frac{\mathrm{d}f_{e}(\boldsymbol{k}_{e})}{\mathrm{d}t}\right)_{form} = -\sum_{\boldsymbol{k}_{T},\boldsymbol{k}_{e}} F_{\boldsymbol{k}_{X},\boldsymbol{k}_{e}\to\boldsymbol{k}_{T}} f_{X}(\boldsymbol{k}_{X}) f_{e}(\boldsymbol{k}_{e}),$$
(31)

Parameter	Symbol	Value	Unit
Band gap energy	E_g	1519	meV
Electron effective mass	m_e	0.08	m_0
Heavy hole effective mass	m_{hh}	0.17	m_0
LO phonon energy	$\hbar\omega_{LO}$	36	meV
Static dielectric constant	ϵ_0	12.85	
High frequency dielectric constant	ϵ_{∞}	10.88	
Crystal density	ρ	5.3162	g·cm ⁻³
Sound velocity	v_s	4726.5	$m \cdot s^{-1}$
Conduction band deformation potential	a_e	-7.0	eV
Valence band deformation potential	a_h	3.5	eV
Exciton binding energy	E_T	6.5	meV
Trion binding energy	E_T	1.77	meV
Exciton Bohr radius	λ_X	11.0	nm
Trion variational parameter $\#1(X^{-})$	λ_T	15	nm
Trion variational parameter $\#2(X^{-})$	λ'_T	30.0	nm
Trion variational parameter $\#1(X^+)$	λ_T	16	nm
Trion variational parameter $\#2(X^+)$	λ_T'	25.0	nm

TABLE I: GaAs Material Parameters

where $F_{\mathbf{k}_h, \mathbf{k}_e \to \mathbf{k}_T}$ represents the probability per unit time for a bound electron-hole pair and a free electron to bind together and form an exciton. We assume that bound and unbound carriers are thermalized and use Boltzmann distribution function $f_X(k_X)$ and $f_e(k_e)$ for exciton and electron population, respectively. By summing Eq. (31) over \mathbf{k}_e , we obtain an adiabatic equation for the evolution of the electron density

$$\frac{\mathrm{d}n_{e}}{\mathrm{d}t} = -\sum_{\boldsymbol{k}_{T}} F(\boldsymbol{k}_{T}) n_{X} n_{e} \equiv -A_{2}^{-} n_{X} n_{e}.$$
(32)

The coefficient A_2^- is the bimolecular formation coefficient, which depends on both T_c and the lattice temperature T_l through the term

$$F(\mathbf{k}_{T}) = \left(\frac{2\pi\hbar^2}{k_B T_c}\right)^2 \frac{1}{m_X m_e S} \sum_{\mathbf{k}_X, \mathbf{k}_e} w_{\mathbf{k}_X, \mathbf{k}_e \to \mathbf{k}_T} \quad (33)$$

$$\times e^{-(E_X(\mathbf{k}_X) + E_e(\mathbf{k}_e))/k_B T_c}.$$
(34)

We calculate the formation rate using Fermi's golden rule

$$w_{\mathbf{k}_{X},\mathbf{k}_{e}\rightarrow\mathbf{k}_{T}}^{\pm} = \frac{2\pi}{\hbar} \sum_{\mathbf{q},q_{z}} \left| \langle \mathbf{k}_{T} | \otimes \langle n_{\mathbf{q},q_{z}} \pm 1 | \mathcal{H}_{e/h-ph} | n_{\mathbf{q},q_{z}} \rangle \otimes | \mathbf{k}_{X} \rangle \otimes | \mathbf{k}_{e} \rangle \right|^{2} \times \delta \left[E_{X}(\mathbf{k}_{X}) + E_{e}(\mathbf{k}_{e}) - E_{T}(\mathbf{k}_{T}) \mp \hbar \omega_{ph}(\mathbf{q},q_{z}) \right], \quad (35)$$

with $E_X(\mathbf{k}_X)$, $E_e(\mathbf{k}_e)$ and $E_T(\mathbf{k}_T)$ the energy dispertion of the electrons, holes and excitons respectively, and $\hbar\omega_{ph}(\mathbf{q}, q_z)$ the energy of the emitted (absorbed) phonon. We first build the bound and unbound electron-hole pair states $|\mathbf{k}_T\rangle$ and $|\mathbf{k}_X\rangle \otimes |\mathbf{k}_e\rangle$.

A. Trion state.

The two electrons and the hole are positioned at $(\mathbf{r}_{1\parallel}, z_1)$, $(\mathbf{r}_{2\parallel}, z_2)$ and $(\mathbf{r}_{h\parallel}, z_h)$ respectively, while the center-of-mass (CM) and relative coordinates in the QW plane are now given by $\mathbf{R}_{\parallel} = \alpha_T(\mathbf{r}_{1\parallel} + \mathbf{r}_{2\parallel}) + \beta_T \mathbf{r}_{h\parallel}$ and $\mathbf{r}_{ih\parallel} = \mathbf{r}_{i\parallel} - \mathbf{r}_{h\parallel}$ $(i = 1, 2); \alpha_T = m_e/M_T, \beta_T = m_h/M_T$ and M_T is the trion mass. We consider a simple two parameter Chandrasekhar-type trial envelope function that was successively used to calculate trion-electron scattering¹⁷:

$$\phi^{T}(r_{1\mathrm{h}\parallel}, r_{2\mathrm{h}\parallel}, z_{1}, z_{2}, z_{h})$$

$$= \mathcal{N}_{T}\chi_{e}(z_{1})\chi_{e}(z_{2})\chi_{h}(z_{h})$$

$$[\varphi^{\lambda_{T}}(r_{1\mathrm{h}})\varphi^{\lambda_{T}'}(r_{2\mathrm{h}}) \pm \varphi^{\lambda_{T}'}(r_{1\mathrm{h}})\varphi^{\lambda_{T}}(r_{2\mathrm{h}})], \qquad (36)$$

where the + (-) sign applies to the singlet (triplet) spin configuration and the trion wavefunction normalization factor is given by

$$\mathcal{N}_T = \frac{1}{\sqrt{2(1 \pm \kappa^2)}},\tag{37}$$

with

æ

$$\kappa = \frac{4\lambda\lambda'}{(\lambda + \lambda')^2}.$$
(38)

Its in-plane Fourier transform reads

$$\Phi_{\boldsymbol{k}_1,\boldsymbol{k}_2,\boldsymbol{k}_h}^T(z_1,z_2,z_h) = \delta_{\boldsymbol{k}_T-\boldsymbol{k}_1-\boldsymbol{k}_2-\boldsymbol{k}_h} \phi_{\alpha_T\boldsymbol{k}_T-\boldsymbol{k}_1,\alpha_T\boldsymbol{k}_T-\boldsymbol{k}_2}^T(z_1,z_2,z_h) \quad (39)$$

and the state of a single trion with an in-plane CM momentum \mathbf{k}_T is constructed similarly to that of a single exciton

$$\begin{aligned} \left| \boldsymbol{k}_{T}^{S} \right\rangle &= \sum_{\substack{\boldsymbol{k}_{1}, \boldsymbol{k}_{2} \\ s_{1}, s_{2}}} \int \mathrm{d}z_{1} \,\mathrm{d}z_{2} \,\mathrm{d}z_{h} \,\phi_{\alpha_{T}\boldsymbol{k}_{T}+\boldsymbol{k}_{1},\alpha_{T}\boldsymbol{k}_{T}+\boldsymbol{k}_{2}}^{T*}(z_{1}, z_{2}, z_{h}) \\ &\times \xi_{S}^{*}(s_{1}, s_{2}) \,\hat{c}_{-\boldsymbol{k}_{1}, z_{1}}^{s_{1}\dagger} \hat{c}_{-\boldsymbol{k}_{2}, z_{2}}^{s_{2}\dagger} \hat{d}_{\boldsymbol{k}_{T}+\boldsymbol{k}_{1}+\boldsymbol{k}_{2}, z_{h}}^{\dagger} \left| 0 \right\rangle, \end{aligned}$$
(40)

where we have added the spin index to the electron creation operator and introduced $\xi_S(s_1, s_2) = \langle S | s_1, s_2 \rangle$ the projection of a generic spin configuration of two electrons on the singlet spin configuration. The in-plane Fourier transform of the trion singlet wavefunction in Eq. (39) is given by

$$\varphi_{\boldsymbol{k}_{1},\boldsymbol{k}_{2}}^{T*}(z_{1},z_{2},z_{h}) = \mathcal{N}_{T}\chi_{e}(z_{1})\chi_{e}(z_{2})\chi_{h}(z_{h})$$
$$\times \left[\varphi_{\boldsymbol{k}_{1}}^{\lambda_{T}}\varphi_{\boldsymbol{k}_{2}}^{\lambda_{T}} + \varphi_{\boldsymbol{k}_{1}}^{\lambda_{T}'}\varphi_{\boldsymbol{k}_{2}}^{\lambda_{T}}\right], \quad (41)$$

where $\varphi_{k_1}^{\lambda'_T}$ has already been defined in Eq. 9. The exciton-free electron state is given by

$$\begin{aligned} |\mathbf{k}_{X}, \mathbf{k}_{e'}\rangle &= \sum_{\mathbf{k}_{e}} \int \mathrm{d}z_{e} \,\mathrm{d}z_{h} \,\mathrm{d}z'_{e} \,\phi^{*}_{\alpha_{X}\mathbf{k}_{X}+\mathbf{k}_{e}}(z_{e}, z_{h}) \,\psi^{*}_{\mathbf{k}_{e'}}(z_{e'}) \\ &\times \hat{c}^{\dagger}_{-\mathbf{k}_{e}, z_{e}} \hat{d}^{\dagger}_{\mathbf{k}_{X}+\mathbf{k}_{e}, z_{h}} \hat{c}^{\dagger}_{\mathbf{k}_{e'}, z_{e'}} \left|0\right\rangle. \end{aligned} \tag{42} \\ &\mathbf{B}. \quad \mathbf{Matrix element calculation.} \end{aligned}$$

We calculate the matrix elements in (35)

$$\langle \mathbf{k}_{T}^{S}; s_{h}' | \otimes \langle n_{\mathbf{q},q_{z}} \pm 1 | \mathcal{H}_{e/h-ph} | n_{\mathbf{q},q_{z}} + 1 \rangle \otimes | \mathbf{k}_{X}; s_{1}; s_{h} \rangle \otimes | \mathbf{k}_{2}; s_{2} \rangle$$

$$= \sum_{\mathbf{k},s} \sum_{\mathbf{k}_{1}} \sum_{\mathbf{k}_{1}',\mathbf{k}_{2}'} \sum_{s_{1}',s_{2}'} \int dz \ dz_{1} \ dz_{2} \ dz_{h} \ dz_{1}' \ dz_{2}' \ dz_{h}' \sqrt{n_{\mathbf{q},q_{z}} + 1}$$

$$\times \xi_{S}^{*}(s_{1}',s_{2}') \phi_{\alpha_{X}\mathbf{k}_{X}+\mathbf{k}_{1}}^{X}(z_{1},z_{h}) \psi_{\mathbf{k}_{2}}(z_{2}) \phi_{\alpha_{T}\mathbf{k}_{T}+\mathbf{k}_{1}',\alpha_{T}\mathbf{k}_{T}+\mathbf{k}_{2}'}(z_{1}',z_{2}',z_{h}') e^{iq_{z}z}$$

$$\times \left[V_{\mathbf{q},q_{z}}^{e} \langle 0| \ \hat{c}_{1} \ \hat{c}_{2} \ \hat{c}_{3}^{\dagger} \ \hat{c}_{4} \ \hat{c}_{5}^{\dagger} \ \hat{c}_{6}^{\dagger} \ | 0 \rangle \langle 0| \ \hat{d}_{7} \ \hat{d}_{8}^{\dagger} \ | 0 \rangle - V_{\mathbf{q},q_{z}}^{h} \langle 0| \ \hat{c}_{1} \ \hat{c}_{2} \ \hat{c}_{5}^{\dagger} \ \hat{c}_{6}^{\dagger} \ | 0 \rangle \langle 0| \ \hat{d}_{7} \ \hat{d}_{8}^{\dagger} \ | 0 \rangle - V_{\mathbf{q},q_{z}}^{h} \langle 0| \ \hat{c}_{1} \ \hat{c}_{2} \ \hat{c}_{5}^{\dagger} \ \hat{c}_{6}^{\dagger} \ | 0 \rangle \langle 0| \ \hat{d}_{7} \ \hat{d}_{8}^{\dagger} \ | 0 \rangle \right].$$
(43)

where we simplified the operators index using the following scheme

$$1 = (-\mathbf{k}'_1, z'_1, s'_1)
4 = (\mathbf{k}, z, s)
7 = (\mathbf{k}_T + \mathbf{k}'_1 + \mathbf{k}'_2, z'_h, s'_h)
2 = (-\mathbf{k}'_2, z'_2, s'_2)
5 = (-\mathbf{k}_1, z_1, s_1)
8 = (\mathbf{k}_X + \mathbf{k}_1, z_h, s_h)
3 = (\mathbf{k} + \mathbf{q}, z, s)
6 = (\mathbf{k}_2, z_2, s_2)
8 = (\mathbf{k}_X + \mathbf{k}_1, z_h, s_h)$$

Using the electron, holes anti-commutation relations, the Fermi vacuum expectation value of the operators read

$$\langle 0| \hat{c}_1 \hat{c}_2 \hat{c}_3^{\dagger} \hat{c}_4 \hat{c}_5^{\dagger} \hat{c}_6^{\dagger} |0\rangle = \delta_{13} (\delta_{25} \delta_{46} - \delta_{26} \delta_{45}) - \delta_{23} (\delta_{15} \delta_{46} - \delta_{16} \delta_{45}) \tag{44}$$

$$\langle 0|\,\hat{d}_7^{}\hat{d}_8^{\dagger}\,|0\rangle = \delta_{78} \tag{45}$$

$$\langle 0| \, \hat{c}_1 \hat{c}_2 \hat{c}_5^{\dagger} \hat{c}_6^{\dagger} \, |0\rangle = \delta_{25} \delta_{16} - \delta_{15} \delta_{26} \tag{46}$$

$$\langle 0|\,\hat{d}_7 \hat{d}_3^\dagger \hat{d}_4 \hat{d}_8^\dagger \,|0\rangle = \delta_{37} \delta_{48} \tag{47}$$

Using the later results in Eq. (43) gives

$$\langle \boldsymbol{k}_{T}^{S}; \boldsymbol{s}_{h}^{\prime} | \otimes \langle \boldsymbol{n}_{\boldsymbol{q},q_{z}} \pm 1 | \mathcal{H}_{e/h-ph} | \boldsymbol{n}_{\boldsymbol{q},q_{z}} \rangle \otimes | \boldsymbol{k}_{X}; \boldsymbol{s}_{1}; \boldsymbol{s}_{h} \rangle \otimes | \boldsymbol{k}_{2}; \boldsymbol{s}_{2} \rangle$$

$$= [\xi_{S}^{*}(\boldsymbol{s}_{2},\boldsymbol{s}_{1}) - \xi_{S}^{*}(\boldsymbol{s}_{1},\boldsymbol{s}_{2})] \delta_{\boldsymbol{s}_{h},\boldsymbol{s}_{h}^{\prime}} \sqrt{\boldsymbol{n}_{\boldsymbol{q},q_{z}} + 1/2 \pm 1/2} \sum_{\boldsymbol{k}_{1}} \phi_{\alpha_{X}\boldsymbol{k}_{X}+\boldsymbol{k}_{1}}^{X}$$

$$\times \left\{ V_{\boldsymbol{q},q_{z}}^{e} I_{e}(q_{z}) [\phi_{\alpha_{T}\boldsymbol{k}_{T}-\boldsymbol{k}_{2},\alpha_{T}\boldsymbol{k}_{T}+\boldsymbol{k}_{1}+\boldsymbol{q}} + \phi_{\alpha_{T}\boldsymbol{k}_{T}-\boldsymbol{k}_{2}+\boldsymbol{q},\alpha_{T}\boldsymbol{k}_{T}+\boldsymbol{k}_{1}}] - V_{\boldsymbol{q},q_{z}}^{h} I_{h}(q_{z}) \phi_{\alpha_{T}\boldsymbol{k}_{T}-\boldsymbol{k}_{2},\alpha_{T}\boldsymbol{k}_{T}+\boldsymbol{k}_{1}} \right\} \delta_{\boldsymbol{q},\boldsymbol{k}_{X}+\boldsymbol{k}_{2}-\boldsymbol{k}_{T}}.$$

$$(48)$$

Finally, for parabolic electron, exciton and trion dispersion, the probability transition (35) is

$$w_{\mathbf{k}_{X},\mathbf{k}_{2}\to\mathbf{k}_{T}}^{\pm} = \frac{2\pi}{\hbar} \sum_{\mathbf{q},q_{z}} (n_{\mathbf{q},q_{z}} + \frac{1}{2} \pm \frac{1}{2}) \\ \times \left| \sum_{\mathbf{k}_{1}} V_{\mathbf{q},q_{z}}^{e} I_{e}(q_{z}) [\phi_{\alpha_{T}\mathbf{k}_{T}-\mathbf{k}_{2},\alpha_{T}\mathbf{k}_{T}+\mathbf{k}_{1}+\mathbf{q}} + \phi_{\alpha_{T}\mathbf{k}_{T}-\mathbf{k}_{2}+\mathbf{q},\alpha_{T}\mathbf{k}_{T}+\mathbf{k}_{1}}] - V_{\mathbf{q},q_{z}}^{h} I_{h}(q_{z}) \phi_{\alpha_{T}\mathbf{k}_{T}-\mathbf{k}_{2},\alpha_{T}\mathbf{k}_{T}+\mathbf{k}_{1}} \right|^{2} \\ \times \delta \left[\frac{\hbar^{2}k_{X}^{2}}{2M_{X}} + \frac{\hbar^{2}k_{2}^{2}}{2m_{e}} + E_{T} - \frac{\hbar^{2}k_{T}^{2}}{2M_{T}} \mp \hbar\omega_{ph}(\mathbf{q},q_{z}) \right] \delta_{\pm\mathbf{q},\mathbf{k}_{X}+\mathbf{k}_{2}-\mathbf{k}_{T}}, \quad (49)$$

where we averaged over the initial electron spin states and exciton angular momentum states.

IV. TRIMOLECULAR FORMATION OF TRIONS

Again, we write the scattering term in the Boltzmann equation process

$$\left(\frac{\mathrm{d}f_{e}(\boldsymbol{k}_{e})}{\mathrm{d}t}\right)_{form} = -\sum_{\boldsymbol{k}_{T},\boldsymbol{k}_{e}'} F_{\boldsymbol{k}_{e},\boldsymbol{k}_{e}',\boldsymbol{k}_{h}\to\boldsymbol{k}_{T}} f_{e}(\boldsymbol{k}_{e}) f_{e}(\boldsymbol{k}_{e}') f_{h}(\boldsymbol{k}_{h})$$
(50)

where $F_{\mathbf{k}_e,\mathbf{k}'_e,\mathbf{k}_h\to\mathbf{k}_T}$ represents the probability per unit time for two free electrons and one free hole to bind together and form an exciton. We assume that bound and unbound carriers are thermalized and use Boltzmann distribution function $f_X(k_e)$ and $f_h(k_h)$ for exciton and electron population, respectively. By summing Eq. (50) over

$$\mathbf{k}_{e}$$
, we obtain an adiabatic equation for the evolution of the electron density

$$\frac{\mathrm{d}n_e}{\mathrm{d}t} = -\sum_{\boldsymbol{k_T}} F(\boldsymbol{k_T}) n_e^2 n_h \equiv -A_3^- n_e^2 n_h.$$
(51)

The coefficient A_3^- is the trimolecular formation coeffi-),cient, which depends on both T_c and the lattice temperature T_l through the term

$$F(\mathbf{k}_{T}) = \left(\frac{2\pi\hbar^{2}}{k_{B}T_{c}}\right)^{3} \frac{1}{m_{e}^{2}m_{h}S^{3/2}} \sum_{\mathbf{k}_{e},\mathbf{k}_{e}',\mathbf{k}_{h}} w_{\mathbf{k}_{e},\mathbf{k}_{e},\mathbf{k}_{h}'\to\mathbf{k}_{T}}$$
$$\times e^{-(E_{e}(\mathbf{k}_{e})+E_{e}(\mathbf{k}_{e}')+E_{h}(\mathbf{k}_{h}))/k_{B}T_{c}}.$$
(52)

We calculate the formation rate using Fermi's golden rule

$$w_{\boldsymbol{k}_{e},\boldsymbol{k}_{e}',\boldsymbol{k}_{h}\rightarrow\boldsymbol{k}_{T}}^{\pm} = \frac{2\pi}{\hbar} \sum_{\boldsymbol{q},q_{z}} \left| \langle \boldsymbol{k}_{T} | \otimes \langle n_{\boldsymbol{q},q_{z}} \pm 1 | \mathcal{H}_{e/h-ph} | n_{\boldsymbol{q},q_{z}} \rangle \otimes | \boldsymbol{k}_{e} \rangle \otimes | \boldsymbol{k}_{e} \rangle \otimes | \boldsymbol{k}_{h} \rangle \right|^{2} \\ \times \delta \left[E_{e}(\boldsymbol{k}_{e}) + E_{e}(\boldsymbol{k}_{e}') + E_{h}(\boldsymbol{k}_{h}) - E_{T}(\boldsymbol{k}_{T}) \mp \hbar \omega_{ph}(\boldsymbol{q},q_{z}) \right], \quad (53)$$

with $E_X(\mathbf{k}_X)$, $E_e(\mathbf{k}_e)$ and $E_T(\mathbf{k}_T)$ the energy dispertion of the electrons, holes and excitons respectively, and $\hbar\omega_{ph}(\mathbf{q}, q_z)$ the energy of the emitted (absorbed) phonon. Finally, for parabolic electron, exciton and trion dispersion, the probability transition 53 becomes

$$w_{\mathbf{k}_{e},\mathbf{k}_{e}',\mathbf{k}_{h}\to\mathbf{k}_{T}}^{\pm} = \frac{2\pi}{\hbar} \sum_{\mathbf{q},q_{z}} (n_{\mathbf{q},q_{z}} + \frac{1}{2} \pm \frac{1}{2}) \\ \times \left| V_{\mathbf{q},q_{z}}^{e} I_{e}(q_{z}) [\phi_{\alpha_{T}\mathbf{k}_{T}-\mathbf{k}_{2},\alpha_{T}\mathbf{k}_{T}+\mathbf{k}_{1}+\mathbf{q}} + \phi_{\alpha_{T}\mathbf{k}_{T}-\mathbf{k}_{2}+\mathbf{q},\alpha_{T}\mathbf{k}_{T}+\mathbf{k}_{1}}^{T*}] - V_{\mathbf{q},q_{z}}^{h} I_{h}(q_{z}) \phi_{\alpha_{T}\mathbf{k}_{T}-\mathbf{k}_{2},\alpha_{T}\mathbf{k}_{T}+\mathbf{k}_{1}} \right|^{2} \\ \times \delta \left[\frac{\hbar^{2}k_{e}^{2}}{2m_{e}} + \frac{\hbar^{2}k_{e}^{\prime2}}{2m_{e}} + \frac{\hbar^{2}k_{h}^{2}}{2m_{h}} + E_{T} - \frac{\hbar^{2}k_{T}^{2}}{2M_{T}} \mp \hbar\omega_{ph}(\mathbf{q},q_{z}) \right] \delta_{\pm\mathbf{q},\mathbf{k}_{X}+\mathbf{k}_{2}-\mathbf{k}_{T}}, \quad (54)$$

A. Numerical results



FIG. 2: The bi- and tri- molecular trion formation coefficients A_2^{α} and A_3^{α} as a function of the inverse carrier temperature as calculated from our model for LA phonon assisted formation. The red curve indicates X^+ formation and the blue curve X^- formation.

In Fig. 2, we represent the results of our numerical calculation for LA phonon assisted formation. We stress the fact that the results for LO phonons are orders of magnitude smaller and consequently negligible for bi- and tri-molecular processes. This shows that the exclusive formation mechanism for trions is governed by LA phonon interaction. We predict a decrease of the bior tri-molecular formation for raising temperatures. We also demonstrate that the bi and tri-molecular formation coefficients for negatively and positively charged excitons are approximatively equal $(A_2^+ = A_2^-)$ and $(A_3^+ = A_3^-)$.

A more accurate calculation should rely on a better trion wavefunction. The Chandrashekar variational function is most likely to simple to yield quantitative results. We note however that electron-trion scattering¹⁸ will contribute to ionize trions. This effect will dramatically increase at high temperatures. We consequently propose that the electron-trion scattering reduce the experimental values for the trion formation coefficients.

V. FORMATION RATES CLOSE TO EQUILIBRIUM

In this Section, we propose to derive formation rate for electrons, holes, excitons and trions assuming thermodynamical equilibrium. In this set of equations, we neglect both biexciton channels and Auger channels because experiments on undoped samples demonstrate that, at the densities considered in the present work, these channels are not significant⁸.

The dynamics of a plasma of electrons containing electrons (e), holes (h), excitons (X) and trions $(X^+$ and $X^-)$ is governed by the following five channels:

$e + h \leftrightarrow X$	
$X + e \leftrightarrow X^-$	$X + h \leftrightarrow X^+$
$2e + h \leftrightarrow X^{-}$	$2h + e \leftrightarrow X^+$

The different formation rates for these populations read

$$F^X = C\mathbf{n}\mathbf{p} - \gamma CK_X \mathbf{X},\tag{55}$$

$$F_2^{X^-} = A_2^- \mathbf{X} \mathbf{n} - A_2^- K_2^- \mathbf{X}^-, \tag{56}$$

$$F_3^{X^-} = A_3^- \mathbf{nnp} - A_3^- K_3^- \mathbf{X}^-, \tag{57}$$

$$F_2^{X^+} = A_2^+ \mathbf{X} \mathbf{p} - A_2^+ K_2^+ \mathbf{X}^+, \qquad (58)$$

$$F_3^{X^+} = A_3^+ \mathbf{npp} - A_3^+ K_3^+ \mathbf{X}^+, \tag{59}$$

where C, A_2^{α} and A_3^{α} are respectively the exciton, trion bimolecular and trion trimolecular formation rate calculated in this article; E_{bX} is the exciton binding energy; K_X , K_2^{α} , K_3^{α} the equilibrium coefficients. For a 2D system, they can be derived from the Boltzmann distribution

$$n_{\alpha} = 2g_{\alpha} \int \frac{d^2k}{2\pi} e^{-hbar^2k^2/2m_{\alpha}k_BT} = g_{\alpha} \frac{m_{\alpha}k_BT}{2\pi\hbar^2} e^{-\mu_{\alpha}/K_BT}$$
(60)

where $\alpha = e, h, X, T$, the factor $g_{\alpha} = 2$ is the spin degeneracy of the electron, hole, exction and trion in the non degenerate regime, where Boltzmann statistics applies.

Using that fact that the chemical potential of the exciton μ_X is related to the chemical potential of electrons μ_e and holes μ_h as $\mu_X = \mu_e + \mu_h + E_X$ (E_X is here defined as minus the exciton binding energy), one immediately obtains the Saha relation for the exciton density

$$\frac{np}{X} = K_X(T) = \frac{g_e g_h}{g_X} \frac{m_e m_h}{m_X} \frac{k_B T}{2\pi\hbar^2} e^{-E_X/k_B T}.$$
 (61)

Similarly, the chemical potential of the trions is $\mu_T = 2\mu_e + \mu_h + E_T$ (E_T is here defined as minus the trion binding energy), so that Saha equations for trion bi-molecular formation are

$$\frac{Xn}{X^{-}} = K_{2}^{-}(T) = \frac{g_{e}^{2}g_{X}}{g_{T}} \frac{m_{X}m_{e}}{m_{X^{-}}} \frac{k_{B}T}{2\pi\hbar^{2}} e^{-(E_{T}-E_{X})/k_{B}T}$$
(62)

$$\frac{Xp}{X^+} = K_2^+(T) = \frac{g_h^2 g_X}{g_T} \frac{m_X m_h}{m_{X^+}} \frac{k_B T}{2\pi\hbar^2} e^{-(E_T - E_X)/k_B T}$$
(63)

Finally, the following set of equation is inferred for tri-molecular formation:

$$\frac{n^2h}{X^-} = K_3^-(T) = \frac{g_e^2 g_h}{g_T} \frac{m_e^2 m_h}{m_{X^-}} \left(\frac{k_B T}{2\pi\hbar^2}\right)^2 e^{-E_T/k_B T}$$
(64)

$$\frac{n\hbar^2}{X^+} = K_3^+(T) = \frac{g_e g_h^2}{g_T} \frac{m_e m_h^2}{m_{X^+}} \left(\frac{k_B T}{2\pi\hbar^2}\right)^2 e^{-E_T/k_B T}$$
(65)

Such a set of equations, together with the equilibrium densities, allow to compute the dynamics of the different populations after non-resonant optical excitation. This may apply both to undoped⁸ as well as to doped quantum wells. The results in the case of a sample doped with electrons will be detailed in another publication¹³. The experiments show that indeed, when the density of electrons is sufficient and at excitation densities of the order of 10^{10} cm⁻² and above, the trimolecular formation process of trions has to be taken into account to properly reproduce the observed dynamics.

VI. CONCLUSION

In this paper, we have derived the appropriate model for computing the rates for exciton and trion formation. For the case of trions, we have derived the equations for both the bi- and tri-molecular phonon-assisted formation

- ¹ C. Weisbuch, R. C. Miller, R. Dingle, A. C. Gossard, and W. Wiegman, Solid State Communications **37**, 219 (1981), ISSN 0038-1098.
- ² B. Deveaud, T. C. Damen, J. Shah, and C. W. Tu, Applied Physics Letters **51**, 828 (1987).
- ³ H. W. Yoon, D. R. Wake, and J. P. Wolfe, Phys. Rev. B 54, 2763 (1996).
- ⁴ T. C. Damen, J. Shah, D. Y. Oberli, D. S. Chemla, J. E. Cunningham, and J. M. Kuo, Phys. Rev. B **42**, 7434 (1990).
- ⁵ D. Robart, X. Marie, B. Baylac, T. Amand, M. Brousseau, G. Bacquet, G. Debart, R. Planel, and J. M. Gerard, Solid State Communications **95**, 287 (1995), ISSN 0038-1098.
- ⁶ B. Deveaud, J. Phys. IV **3**, 11 (1993).
- ⁷ R. A. Kaindl, M. A. Carnahan, D. Hagele, R. Lovenich, and D. S. Chemla, Nature **423**, 734 (2003).
- ⁸ J. Szczytko, L. Kappei, J. Berney, F. Morier-Genoud, M. T. Portella-Oberli, and B. Deveaud, Phys. Rev. Lett. 93, 137401 (2004).
- ⁹ J. Szczytko, L. Kappei, J. Berney, F. Morier-Genoud, M. T. Portella-Oberli, and B. Deveaud, Physical Review B **71**, 195313 (2005).
- ¹⁰ A. Thilagam and J. Singh, Physical Review B 48, 4636

mation rate of negatively and positively charged excitons have similar orders of magnitude for densities that are used in the experiments. We have then developed the set of relations and the equilibrium conditions allowing to calculate the dynamics of free carriers, excitons and trions. Our results are in very reasonable agreement with recent experiments and allow to confirm that, indeed, trimolecular trion formation may not be neglected in real samples.

of trions. We have shown that bi- and tri-molecular for-

VII. ACKNOWLEDGMENTS

We wish to thank Fabienne Michelini, Michiel Wouters, Christiano Ciuti, Carlo Piermarocchi and Vicenzo Savona for fruitful discussions. We also thank the Swiss National Fundation for funding.

(1993).

- ¹¹ C. Piermarocchi, F. Tassone, V. Savona, A. Quattropani, and P. Schwendimann, Phys. Rev. B 53, 15834 (1996).
- ¹² C. Piermarocchi, F. Tassone, V. Savona, A. Quattropani, and P. Schwendimann, Phys. Rev. B 55, 1333 (1997).
- ¹³ M. T. Portella-Oberli, J. Berney, L. Kappei, F. Morier-Genoud, J. Szczytko, and B. Deveaud, submitted to Phys. Rev. Lett. (2009).
- ¹⁴ W. H. Knox, Optical Studies of Femtosecond Carrier Thermalization in GaAs (Academic Press, San Diego, 1992), p. 313.
- ¹⁵ G. Bastard, Wave mechanics applied to semiconductor heterostrutures (Les éditions de physique, Les Ulis, France, 1988).
- ¹⁶ G. D. Mahan, Many Particle Physics (Springer, 2000), 3rd ed.
- ¹⁷ J. Berney, M. T. Portella-Oberli, and B. Deveaud, Physical Review B (Condensed Matter and Materials Physics) **77**, 121301 (pages 4) (2008).
- ¹⁸ G. Ramon, A. Mann, and E. Cohen, Physical Review B 67, 45323 (2003).