Unifying the Temperature Dependent Dynamics of Glasses

Joseph B. Schlenoff^{*1} and Khalil Akkaoui¹

¹Department of Chemistry and Biochemistry, The Florida State University, Tallahassee, Florida 32306-4390, United States

Abstract

Strong changes in bulk properties, such as modulus and viscosity, are observed near the glass transition temperature, T_g , of amorphous materials. For more than a century, intense efforts have been made to define a microscopic origin for these macroscopic changes in properties. Using transition state theory, we delve into the atomic/molecular level picture of how microscopic localized relaxations, or "cage rattles," translate to macroscopic structural relaxations above T_g . Unit motion is broken down into two populations: (1) simultaneous rearrangement occurs among a critical number of units, n_a , which ranges from 1 to 4, allowing a systematic classification of glasses that is compared to fragility; (2) near T_g , adjacent units provide additional free volume for rearrangement, not simultaneously, but within the "primitive" lifetime, τ_1 , of one unit rattling in its cage. Relaxation maps illustrate how Johari-Goldstein β relaxations stem from the rattle of n_a units. We analyzed a wide variety of glassy materials, and materials with glassy response, using literature data. Our four-parameter equation fits "strong" and "weak" glasses over the entire range of temperatures and also extends to other glassy systems, such as ion-transporting polymers and ferroelectric relaxors. The role of activation entropy in boosting preexponential factors to high "unphysical" apparent frequencies is discussed.

Introduction

Below their glass transition temperature, T_g , amorphous materials exist in a glassy state without long range order. A molecular scale description of the approach to this state from high temperatures, signaled by a rapid increase in bulk stiffness, has long challenged theorists.¹⁻⁴ Figure 1 illustrates the dilemma: at sufficiently high temperature, T, the bulk structural relaxation rate, ω_{α} , mirrored by the viscosity, η , shows classical Arrhenius behavior $ln\omega_{\alpha} \sim -1/T$, typically used to describe thermally activated processes. Approaching T_g , in the "supercooled" region there is a strong deviation from Arrhenius, and at T_g the material becomes a solid glass with almost no liquid-like response.⁵ It is generally agreed that cooperative motion between units comprising the glass increasingly limit dynamics approaching T_g .⁶⁻⁷



Figure 1. Relaxations in glass formers. The dynamics, given by the structural relaxation rate ω_{α} (s⁻¹), or viscosity η (Pa s), slow as it cools. At high temperatures, dynamics can be described by an Arrhenius equation (dashed lines). Deviation from Arrhenius behavior is observed approaching T_g (diamond).

A major goal of theory is to describe dynamics in all glass formers with one equation.¹ Towards this goal, "universal" scalings and relationships have been established. For example, the α -relaxation of many glass formers adheres to thermodynamic scaling: ω_{α} is a function of a scaled relationship between density (pressure) and temperature.⁸⁻⁹ While activation energy E_a and a prefactor A are the only two fit parameters required to describe Arrhenius response, the most economical analytical description of the curvature in the supercooled region needs at least three parameters. Towards this end, the Vogel-Fulcher-Tammann (VFT) equation has been used for several decades;¹⁰

$$\omega_{T,VFT} = \omega_{0,VFT} e^{\frac{-DT_o}{T-T_o}}$$
[1]

where $\omega_{0,VFT}$, D, and T_o are empirical, freely-adjustable fit parameters. ω_0 (η_0) comes from a high-temperature extrapolation. T₀, known as the Vogel temperature, is usually about 50 K below T_g. Many

decades of discussion and controversy have ensued over the meaning of T_0 and whether, as it implies, flow ceases completely at this temperature.¹¹ VFT fits with one set of parameters are typically useful over a limited temperature range. If the range is expanded, two or more VFT fits,¹²⁻¹⁴ or a combination of Arrhenius plus VFT,¹⁵ are often used. Many of the models describing the temperature dependence of structural relaxation have recently been summarized by Novikov and Sokolov.¹⁶

Eyring modified his transition state theory (TST) to describe the viscosity of liquids¹⁷

$$\eta = \kappa \eta_0 e^{-\Delta S^*/R} e^{\Delta H^*/RT}$$
^[2]

where $E_a = \Delta H^* - T\Delta S^*$, and ΔH^* and ΔS^* are enthalpy and entropy of activation, respectively. κ is a transmission coefficient which represent a probability of reaction. Eyring assumed¹⁷ that κ was "probably very nearly unity." Prefactor η_0 was estimated to be N_Ah/V where N_A is Avogadro's number, V the molal volume and h is Planck's constant. In a transition state model, Avramov and Milchev, AM, assumed that dynamics resulted from hopping of units between coordination spheres with a random distribution of activation energies and relaxation time, τ , around a mean.¹⁸ This introduced dynamic heterogeneity and yielded the following three-parameter expression

$$log\eta = log\eta_0 + \left[\frac{\tau}{T}\right]^{\alpha}$$
^[3]

Maxwell's equation relates relaxation rate to viscosity via the high frequency glassy modulus G_0 : $\omega_0 = G_0/\eta_0$. Extrapolations of AM to high temperatures (i.e. into the Arrhenius region) significantly overestimate η_0 , which should be of order 10^{-2} Pa s.¹¹ Hrma et. al recently concluded¹⁹ that any analytical model representing a full 11-12 orders of dynamic range in viscosity or relaxation time, from T_g up, must have at least four adjustable parameters.

Macedo and Litovitz²⁰ focused on the deviation from Arrhenius in the supercooled region by breaking down the jump probability of a molecule to an empty site, p_j , into the probability of having sufficient energy to break bonds p_E (which is the $e^{-\frac{Ea}{RT}}$ term) and the probability that there is sufficient local free volume for a jump to occur, p_v

$$p_j = p_E \times p_v \tag{4}$$

For the p_v term they employed the expression of Cohen and Turnbull²¹ for the probability of finding the minimum local free volume for a jump

$$p_{\nu} = e^{-\gamma \nu_0 / \nu_f} \tag{5}$$

Where γ is an overlap correction between 0.5 and 1, v_0 is the close-packed molecular volume and v_f is the free volume. This yields the following

$$\eta = \eta_0 e^{\gamma v_0 / v_f} e^{E_a / RT}$$
^[6]

This "hybrid" 5-term equation was able to fit both the supercooled and Arrhenius region of the glasses tested.

An expression by Mauro et al.²², previously proposed empirically by Waterton,²³ was derived starting from the Adam-Gibbs (AG) equation relating the configurational entropy, S_c , of a glass former to the viscosity²⁴

$$ln\eta = ln\eta_0 + \frac{E_a s_c^*}{RTS_c}$$
[7]

where s_c^* is a constant high temperature configurational entropy (found in the Arrhenius region) and S_c decreases into the supercooled region. Calculating²⁵⁻²⁶ or measuring²⁷ S_c is not straightforward. Mauro et al. used a temperature-dependent constraint model to obtain S_c, assumed the glass transition was defined by a shear viscosity of 10¹² Pa s, and used experimental slopes of log η vs. 1/T at T_g (known as "fragilities" ²⁸) to arrive at an equation of the form

$$\log\eta = \log\eta_0 + \frac{\kappa}{T} e^{C/T}$$
[8]

Where K and C are constants. A comparison with VFT and AM models concluded that Eq. 8 provided a more accurate description.²² However, all the above three-parameter equations fail to some extent into the Arrhenius region.¹⁹

Adam and Gibbs²⁴ recognized the central importance of correlating molecular (microscopic) motion to structural (bulk) relaxation in glass formers when they ascribed the temperature dependent relaxation rates, $\omega_{\alpha,AG}$ to rearrangements in microstructures termed cooperatively rearranging regions (CRRs) of minimum size n_T units (which they called z*)²⁴

$$\omega_{\alpha,AG} = A e^{-n_T E_1/RT}$$
^[9]

where E_1 is the activation energy for one unit. At temperatures closer to the glass transition, the apparent activation energy $n_T E_1$ (see the slopes in Figure 2) increases substantially, becoming larger than the enthalpy of vaporization by almost a factor of 5.^{24, 29} The increase in apparent E_a is interpreted to stem from increased cooperativity between units.²⁴



Figure 2. In ω_{α} (s⁻¹) as a function of 1/T; solid blue curve. Near the glass transition, n_T cooperatively rearranging units present an increasing *apparent* energy barrier of height n_TE₁ (dashed red lines), where E₁ is the activation energy for one unit. The prefactor A_{n(T)} also increases strongly with n_T on these Arrhenius plots.

The configurational entropy-based approach in Equation 7 is appealing because the activation energy and $log\eta_0$ terms remain constant, leaving the configurational entropy to be determined. In contrast, in the AG dynamic cooperativity framework (Equation 9) each of the Arrhenius-style plots (Figure 2) has slope n_TE_1 but also a different A intercept which depends on n_T . These values of A can be enormous and complicate the original AG approach, which assumed a constant preexponential factor.²⁴

In the present work, we re-evaluate the CRR aspects of the AG microscopic model in a transition state theory framework and add a crucial refinement to the idea that local motion on the microscopic scale is described as "caged" motion, where units "rattle" locally to the limits of their cage, but not beyond.^{4, 30} Under the right conditions, units escape their cages and rearrange - a structural change impacting bulk properties (e.g. viscosity and modulus). In our analysis, we break cooperative motion down into two types: a small number of correlated units rearranges *simultaneously*, facilitated in the supercooled region by neighbors that move *within the relaxation time of one unit cage rattle*. Separating the microscopic components in this way allows us to separate the *spatial* and *temporal* elements of the α -relaxation and show how localized caged motion evolves into structural relaxation.

Methods and Model

Single Units. At the microscopic level a material consists of single units of minimum size, often presented as beads in simulations.^{3, 30-31} At all temperatures above zero, each unit oscillates from its average local position at an *average* (relaxation) rate ω_1

$$\omega_1 = A_1 e^{-E_1/RT} \tag{10}$$

with activation energy E_1 and preexponential factor A_1 . This frequency refers to units rattling to the limit of their transient cages⁴ with an *average* temperature dependent relaxation time $\tau_1 = 1/\omega_1$. In other words, a fraction of units, given by the Boltzmann distribution, $e^{-E_1/RT}$, has enough energy to move to the limit of their cage. The probability that a *specific* unit will move in its cage during time interval τ_1 is 1/e from Poisson statistics (see Section S1). Therefore, the probability that n(T) specific neighboring units will move in interval τ_1 is $e^{-n(T)}$.

The Critical Relaxation Cluster, n_{α} Dielectric, mechanical, and thermal methods reveal many relaxation modes in glasses. Johari and Goldstein drew attention to certain relaxations in rigid glasses, β_{JG} , which had the same Arrhenius temperature dependence as the liquid state (at far higher temperatures) and suggested this relaxation corresponded to less cooperative but caged motion of an unspecified number of adjacent or clustered units.³²⁻³³ Ngai and coworkers have stressed the importance of these "primitive relaxations" as precursors to the α -relaxation at T > Tg.^{8, 34} Recent computer simulations have supported the evolution of caged dynamics from far below Tg to unhindered dynamics in the liquid state far above Tg.³⁵

Here, we assume for α -relaxation a cluster of a specific number of units, n_{α} , must rearrange *simultaneously* such that the total energy is the same before and after the move. These n_{α} units, in a local minimum energy environment, are connected by chemical (covalent, ionic, or metallic bonding) or physical (dipolar, hydrogen bonding) interactions, depending on the material, and move to conserve the symmetry and energy of interaction. This (temperature independent) critical number of units is often assumed to be equal to $1,^{24}$ but, as shown here, it can range from 1 to 4. Above T_g , n_{α} units start to rearrange, below T_g , they mostly rattle (see Scheme 1 for an example of $n_{\alpha} = 2$). If n_{α} is the same for α and β_{IG} relaxations, the activation energy for n_{α} units rattling *simultaneously* is $n_{\alpha}E_1 = E_a$, which yields the corresponding Arrhenius form of the *caged* relaxation rate $\omega_{n_{\alpha,rattle}} = \omega_{JG} = A_{JG}e^{-E_{\alpha}/RT}$, where A_{JG} is the prefactor for rattling (see Figure S1, Supplemental Information).



Scheme 1. A. A rattle of two units, which move in a correlated manner to preserve the interaction between them. **B.** Some rattles evolve into a rearrangement, seen as a structural relaxation.

Cooperatively Assisting Units, n_c . When the amplitude of the rattle is enough to overcome the boundaries of the cage, a unit, or a cluster n_{α} of them, may escape. When does a caged relaxation evolve into a structural relaxation? Doolittle and others advanced the idea that the degree of structural mobility is connected directly to the free volume of the material³⁶⁻³⁷ and cooperativity is a consequence of limited free volume.^{7, 38} Thus, n_{α} units require at least V_{α} of free volume to rearrange i.e. to go from caged to structural relaxation (see Section S2). At sufficiently high temperatures (the Arrhenius region) there are no (free volume) constraints to the concerted movement of n_{α} units. α -relaxation occurs with the same slope as caged n_{α} but the intercept is higher because $A_{\alpha} > A_{JG}$. As the temperature decreases, free volume also decreases. At some specific temperature, T_{SA} (SA = super-Arrhenius), at least one of the neighboring units must move to create sufficient free volume during interval τ_1 , which occurs with probability 1/e. This additional unit, and other neighbors that are increasingly called upon as the temperature decreases, are termed "cooperatively assisting," $n_{c(T)}$. Their purpose is to focus the local free volume, which fluctuates spatially and temporally throughout the sample, round n_{α} . Thus, the minimum total number of neighboring units moving cooperatively within τ_1 at any temperature, $n_T = n_{\alpha} + n_{c(T)}$.

T_{SA} marks the start of deviation from Arrhenius response of the α -relaxation where it now enters the spatio-temporally restricted regime. Microstructures of n_{α} units moving while conserving the symmetry of interaction are suggested in Figure 4A - C. From the results below, "simple" molecular glasses with mainly van der Waals intermolecular interactions (no hydrogen bonding) appear to yield $n_{\alpha} = 1$. Polymers appear to be a special case wherein n_{α} is always = 2. For obvious reasons, movement in linear polymers is dimensionally constrained due to the connectivity of the repeat units: only a small segment of the chain, such as the persistence length, can move as a unit. Figure 4D shows the exchange of two polymer segments as a possible example of a $n_{\alpha} = 2$ concerted move. Because the Si atom in silicates shares oxygens with four other Si, the $n_{\alpha} = 4$ found for silicates and related glasses could mean that a "unit" is an oxygen atom. Using high-temperature ²⁹Si NMR measurements of K₂Si₄O₉, relaxation consistent with exchange of oxygens was identified with a total activation energy E_a of 180 kJ mol⁻¹,³⁹ in the range of E_a for silicates listed below.



Figure 4. Relaxation modes. **A & B** caged motion of 1 or 3 units, the latter sampling the extremes of the cage while maintaining its $n_{\alpha} = 3$ interaction environment; **C**) τ_{α} : structural relaxation of $n_{\alpha} = 3$ units facilitated by two neighbors ($n_{c(T)} = 2$) which provide enough free volume for n_{α} units to structurally rearrange. **D**. Possible "unit" exchange in polymers.

There are no preordained n_{α} clusters. Within any τ_1 , any cluster of n_{α} units may attempt to rearrange. Below T_{SA} they are not assured of the free volume needed to rearrange, so they have to rely on $n_{c(T)}$ neighbors to move during τ_1 to provide the required free volume.

Heterogenous Dynamics. Another generally accepted feature of supercooled liquids is that they exhibit spatially heterogenous dynamics,¹⁻³ or regions of different sizes moving at different rates.⁴⁰ In the present analysis, we incorporate the central idea of dynamic heterogeneity as follows: first, there is a spatially- and temporally- fluctuating distribution of sizes in the CRR. Second, as with AG, at any temperature all CRRs above a minimum size, n_T (= $n_{\alpha} + n_{c(T)}$), contribute to bulk α -relaxation:

$$\omega_{\alpha} = A'_{\alpha} e^{-E_{\alpha}/RT} \sum_{n=n_{c(T)}}^{\infty} e^{-n_{T}}$$
[11]

Any CRR of size n_T and above contributes to α -relaxation with weight $e^{-n_{c(T)}}$. The summation is a geometric sum and therefore Equation 11 becomes

$$\omega_{\alpha} = A'_{\alpha} e^{-E_{a}/RT} \frac{e^{1-n_{c(T)}}}{e^{-1}} = A_{\alpha} e^{-E_{a}/RT} e^{-n_{c(T)}}$$
[12]

where $A_{\alpha} = \frac{e}{e-1}A'_{\alpha}$.

In TST, E_a is broken down into activation entropic and enthalpic contributions to the activation barrier. For the unit (n = 1) *rattle*

$$\omega_1 = A_0 e^{\Delta S_1^*/R} e^{-\Delta H_1^*/RT}$$
[13]

and for the n_{α} *rattle*

$$\omega_{JG} = A_0 e^{\Delta S_{JG}^*/R} e^{-\Delta H_{n\alpha}^*/RT}$$
[14]

This presentation makes it clear that the intercept of an Arrhenius plot includes a physical attempt frequency, A_0 , which is assumed to be near the Boson frequency, *and* an activation entropy contribution. Only when ΔS^* is negligible does the A intercept represent an attempt frequency. The (overlooked) importance of ΔS^* has recently been emphasized by Xu et al.⁴¹ The full TST equation for the structural relaxation is

$$\omega_{\alpha} = A_0 e^{\Delta S_{struct}^*/R} e^{-\Delta H_{n\alpha}^*/RT} e^{-n_{c(T)}}$$
^[15]

where ΔS^*_{struct} is the structural activation entropy for n_{α} units and $\Delta H^*_{n\alpha} = n_{\alpha} \Delta H^*_1$. The deviation of ω_{α} from Arrhenius at any temperature is simply a factor of $e^{-n_{c(T)}}$.

Equation 12 shows how relaxation depends on a Boltzmann distribution term, $e^{-E_a/RT}$, representing the steady-state fraction of n_{α} clusters with energy sufficient to overcome barrier E_a , and a statistical term, $e^{-n_{c(T)}}$, stemming from the limiting of free volume with decreasing temperature below

 T_{SA} (free volume continues to increase above T_{SA} but no longer limits the dynamics). A final assumption from Adam and Gibbs²⁴ allows for the substitution of $n_{c(T)}$: the slope of the ω_{α} curve is (see Figure 2)

$$\frac{d\ln\omega_{\alpha}}{dT^{-1}} = -\frac{n_T E_1}{R}$$
[16]

 $n_T E_1$ only *appears* to be a growing activation barrier. It represents the slope of an Arrhenius equation (as in Figure 2) for n_T units rearranging *simultaneously*. In our treatment, only n_{α} units actually rearrange simultaneously. If $n_T E_1$ were the actual barrier, the probability of rearranging at most temperatures would vanishingly small approaching T_g . For example, if A_{α} were 10^{13} s⁻¹, $E_1 = 20$ kJ, $T_g = 300$ K, $n_{Tg} = 13$, then $n_T E_1$ would be 260 kJ and ω_{α} would be about 10^{-21} s⁻¹ instead of approximately 0.01 s⁻¹, as usually seen.

At temperatures greater than T_{SA}, the free volume around n_{α} is enough to allow concerted rearrangement without any contributions from $n_{c(T)}$ units $(n_T \rightarrow n_{\alpha}; n_{c(T)} \rightarrow 0)$ and the frequency attains Arrhenius behavior

$$\omega_{\alpha,Arr} = A_{\alpha} e^{\frac{-E_{\alpha}}{RT}}$$
[17]

 A_{α} is extrapolated from higher temperature measurements where T > T_{SA} as shown in Figure 2 and Figure S1. To minimize the error in measured E_a and A_{α} the temperature should extend as far into the Arrhenius region as possible.

The *deviation* of the measured frequency from the Arrhenius frequency (i.e the frequency calculated at any temperature using Equation 12) is

$$\ln\left(\frac{\omega_{\alpha,Arr}}{\omega_{\alpha}}\right) = n_T - n_{\alpha} = n_{c(T)}$$
^[18]

The number of cooperative units at T_g , n_{Tg} is given by

$$n_{Tg} = \ln \frac{\omega_{\alpha,Arr}}{\omega_{\alpha,Tg}} + n_{\alpha}$$
^[19]

The slope of the linear Arrhenius plot is

$$-\frac{dln\omega_{\alpha,Arr}}{dT^{-1}} = \frac{n_{\alpha}E_1}{R}$$
[20]

where $n_{\alpha}E_1 = E_a$.

Combining Equations 16 and 18 gives a first order differential equation:

$$\frac{d\ln\omega_{\alpha}}{dT^{-1}} - \frac{E_1}{R}\ln\omega_{\alpha} + \frac{E_1}{R}\left(n_{\alpha} + \ln\omega_{\alpha,Arr}\right) = 0$$
[21]

Expanding the Arrhenius term using Equation 17:

$$\frac{d\ln\omega_{\alpha}}{dT^{-1}} - \frac{E_1}{R}\ln\omega_{\alpha} + \frac{E_1}{R}\left(n_{\alpha} + \ln A_{\alpha} - \frac{n_{\alpha}E_1}{RT}\right) = 0$$
[22]

Making the appropriate substitutions yields:

$$\ln \omega_{\alpha} = \ln A_{\alpha} - \frac{n_{\alpha} E_1}{RT} + c_1 e^{\frac{E_1}{RT}}$$
[23]

As $E_a = n_\alpha E_1$, using Equation 17, $\ln A_\alpha - \frac{n_\alpha E_1}{RT} = \ln \omega_{\alpha,Arr}$ which is substituted into Equation 23: $\ln \omega_\alpha = \ln \omega_{\alpha,Arr} + c_1 e^{\frac{E_1}{RT}}$ [24]

To solve for c_1 , a temperature, T_{SA} , where the number of units n_T increases from n_{α} to $n_{\alpha} + 1$ is defined. It describes the divergence of ω_{α} from $\omega_{\alpha,Arr}$ by a factor of 1/e:

$$\ln\left(\frac{\omega_{\alpha,Arr}\left(T_{SA}\right)}{\omega_{\alpha}(T_{SA})}\right) = -c_{1}e^{\frac{E_{1}}{R^{T}_{SA}}} = 1$$
[25]

This allows us to write c_1 as

$$c_1 = -e^{\frac{E_1}{RT_{SA}}}$$
[26]

and substituting E_1 with E_a/n_α finally gives

$$\ln \omega_{\alpha} = \ln \omega_{\alpha,Arr} - exp\left(\frac{E_a}{n_{\alpha}R}\left(\frac{1}{T} - \frac{1}{T_{SA}}\right)\right)$$
[27]

Assuming the temperature range reaches well into the Arrhenius region (reflected by a linear $\ln \omega_{\alpha}$ *versus* 1/T plot) the only parameter which is not directly and uniquely obtained from the data is n_{α} , which remains the only freely adjustable fit parameter, albeit limited to integer values between 1 and 4 (Table 1). We have presented a form of Equation 27 for polymers but, despite excellent agreement with experimental results, we were not able to rationalize each parameter.⁴²

Results

We tested Equation 27 against experimental data from a wide range of glass formers representing the glassy "universe." We used only data which spanned both the high temperature and supercooled regions, giving A_{α} , E_{a} , and T_{SA} experimentally. The impressive agreement is illustrated in Figure 5, with detail on 16 glasses provided in Table 1 (see Figure S2 for individual plots). Classification of glasses is made according to n_{α} in Table 1, which also lists the measured A_{α} , E_{a} and T_{SA} . We emphasize that T_{SA} uniquely occurs at $n_{T} = n_{\alpha} + 1$ and was also taken directly from the data (see Figures S3 and S4 for detail on how E_{a} and T_{SA} were determined). Selection of n_{α} is not arbitrary; Figure S5 shows an example outcome if n_{α} is selected to be ± 1 of its optimal value (Table 1) or if T_{SA} is off by a few degrees. In contrast, reasonable VFT fits may be obtained with widely different combinations of $\omega_{0,VFT}$, D and T_{0} .⁴³

Because T_g in polymers depends on chain length below a certain molecular weight⁴⁴ (ca. 10⁴ Daltons), the values of E_a and T_{SA} also depend somewhat on molecular weight. Unlike polymers, alcohols and metallic glass formers cannot be universally classified under one class as shown in Table 1.

Table 1. Glass formers whose dynamics are reported in Figure 5 and Figure S2 along with their corresponding n_{α} , glass transition temperature (T_g), activation energy (E_a), structural preexponential factor A_{α} , fragility m, T_{SA} and the corresponding references.

| $\mathbf{E_a}$ | | | | | | | | | | | | |
|---|-----------------------|--------------------|-------------------------|--------------------|----------------------------------|---------------------|---------------------------------|--|--|--|--|--|
| Glass Former | \mathbf{n}_{α} | T _g (K) | (kJ mol ⁻¹) | m | n at T _g ^a | Г _{SA} (K) | A_{α} (s ⁻¹) | | | | | |
| o-terphenyl (OTP) ²⁹ | 1 | 240 | 23.7 | 81 ²⁸ | 26 (16) | 335 | 4.71 x 10 ¹² | | | | | |
| Propylene Carbonate (PC) ¹⁵ | 1 | 157 | 14.3 | 132 ²⁸ | 23 (28) | 219 | 1.05 x 10 ¹² | | | | | |
| Polystyrene (PS) ⁴² | 2 | 373 | 106 | 105 ⁴² | 14 (14) | 425 | 3.39 x 10 ¹⁸ | | | | | |
| Poly(vinyl acetate) (PVA) ⁴² | 2 | 313 | 70.6 | 75.8 ⁴² | 13 (13) | 390 | 1.45 x 10 ¹⁶ | | | | | |
| Poly(isobutyl methacrylate) (PiBM) ⁴² | 2 | 328 | 61.6 | 64.5 ⁴² | 13(13) | 421 | 2.83 x 10 ¹⁴ | | | | | |
| Poly(propylene glycol) (PPG) ⁴⁵ | 2 | 206 | 47.9 | 117 ²⁸ | 13 (19) | 250 | 4.55 x 10 ¹⁶ | | | | | |
| Xylitol ⁴⁶ | 2 | 248 | 63.6 | 94 ⁴⁶ | 20 (14) | 311 | 5.25 x 10 ¹⁸ | | | | | |
| 1-methyl-3-butyl-imidazolium ⁴⁷ | 2 | 193 | 30.3 | | 19 | 274 | 1.61 x 10 ¹³ | | | | | |
| Ni _{62.4} Nb _{37.6} ⁴⁸ | 2 | 945 | 165 | 12148 | 26 (27) | 1353 | 5.34 x 10 ¹⁷ | | | | | |
| Ethanol ⁴⁹ | 2 | 97 | 17.5 | 61 ⁴⁹ | 15 (13) | 129 | 4.80 x 10 ¹² | | | | | |

| Pt ₆₀ Ni ₁₅ P ₂₅ ⁴⁸ | 3 | 464 | 67.1 | 67 ⁴⁸ | 25 (27) | 990 | 1.14 x 10 ¹⁶ |
|---|---|-----|------|------------------|---------|------|-------------------------|
| Propanol ⁵⁰ | 4 | 103 | 24.1 | 40 ²⁸ | 12 (13) | 150 | 8.18 x 10 ¹² |
| $Pd_{40}Ni_{40}P_{20}{}^{48}$ | 4 | 554 | 104 | 48 ⁴⁸ | 18 (20) | 1053 | 7.85 x 10 ¹⁵ |
| Sodium Germanate ⁵¹ | 4 | 801 | 250 | 46 ⁵¹ | 14 (11) | 1100 | 4.06 x 10 ¹⁷ |
| Westminster Abbey glass ⁵² | 4 | 592 | 164 | 42 ⁵² | 13 (12) | 810 | 1.56 x 10 ¹⁵ |
| Potassium Silicate ⁵¹ | 4 | 739 | 177 | 33 ⁵¹ | 13 (11) | 1150 | 1.67 x 10 ¹³ |

^an_{Tg} is calculated using Equation 19 at T = T_g and the value in parentheses is estimated using $m = \frac{n_{Tg}E_a}{2.3n_{\alpha}RT_g}$ and literature values for *m* (superscripts are references).



Figure 5. Comparison of Equation 27 to experimental data for different types of glasses as a function of 1/T. The α -relaxation rate, ω_{α} (s⁻¹) of a selection of inorganic, metallic, polymer and small molecule glass formers. Symbols are experimental points from the literature. Solid curves are the results of Equation 27 using the measured parameters listed in Table 1. Only n_{α} is freely adjustable (but must be an integer between 1 and 4).

Discussion

Equation 27 relies on a well-accepted TST foundation with the addition of a statistical term $e^{-n_c(T)}$, which accounts for deviation from Arrhenius. With the Arrhenius slope, T_{SA} and n_a, Equation 27 predicts the entire supercooled region. TST expressions contain a transmission coefficient term, κ , usually assumed to be 1, but is < 1 if some activated complexes do not give rise to products.⁵³ Given the probabilistic derivation of n_{c(T)} it can be thought of as a κ : some groups of n_a units have sufficient energy to rearrange but only a fraction $e^{-n_c(T)} = \kappa$ actually do so. Eyring's assumption¹⁷ that $\kappa = 1$ would thus be correct in the Arrhenius regime far above T_g i.e. in the liquid state.

Criteria for whether a secondary relaxation may be considered a "true" β_{JG} , the precursor to the α -relaxation, have been provided by Ngai and coworkers.^{9,8} In broadband dielectric spectroscopy, BDS, for many glasses, β_{JG} shows up as a high frequency wing or shoulder on the much more intense α -relaxation.⁵⁴ Deconvolution with arbitrary fitting functions may not provide reliable β_{JG} values.⁵⁵ Thus, the use of glass formers with well-distinguished α - and β -peaks in the BDS is preferred, such as the series of polyols sorbitol, threitol and xylitol reported by Döß et al.⁴⁶ Figure 6 shows an example of a relaxation map for xylitol ($n_{\alpha} = 2$). The primitive ω_1 rattle of one unit, with an Arrhenius slope -E₁/R, is the fastest relaxation at all T and extrapolates to A₁ at high T. $\omega_{\beta JG}$ with slope - $n_{\alpha}E_1/R$ describes caged relaxation by n_{α} units.



Figure 6. Relaxation map for xylitol. Structural relaxation rate ω_{α} by cooperative motion among n_T units; open diamonds, experimental from Döß et al.,⁴⁶ solid line from Equation 27 with parameters in Table 1. Unit rattle ω_1 is given in blue. β_{JG} relaxation of caged clusters of n_{α} in yellow dash ($\omega_{\beta JG}$) from Döß et al.⁴⁶ Corresponding intercepts are A_{JG} for the local, caged rattle; and A_{α} for the structural relaxation. A_1 is the intercept for a single unit rattle assumed to be near the Boson peak (although identifying the actual Boson peak from other modes in the ~1 THz range may not be straightforward⁵⁶).

The α -relaxation in the Arrhenius region differs from the linear extrapolation of β_{JG} by a factor $\frac{e^{\Delta S_{struct}^*}}{e^{\Delta S_{JG}^*}}$ (compare Equations 14 and 15). For glasses having $n_{\alpha} = 1$, the difference is small and may suggest that ω_{α} overlaps in the Arrhenius region with an extrapolated $\omega_{\beta JG}$, as was done in Johari's original paper, which extrapolated a β -relaxation near and below T_g to the liquid state.³² Usually, $\omega_{\beta JG}$ merges with ω_{α} at temperature T_{β} where $Rn_{c(T=T\beta)} = \Delta S_{struct}^* - \Delta S_{JG}^*$. If ΔS_{JG}^* and ΔS_{struct}^* are small and $A_0 \approx A_{JG} \approx A_{\alpha}$ then $\omega_{\alpha} \approx \omega_{JG}$. This case is more likely to be satisfied when $n_{\alpha} = 1$. For example, Angell et al. identified a Boson peak in OTP ($n_{\alpha} = 1$) at 18 cm⁻¹ or 5.4 x 10¹¹ Hz x 2 $\pi = 3.4$ x 10¹² s⁻¹ relaxation rate which is close to the A_{α} value in Table 1.⁵⁷ Figure S1 shows the relaxation map for sorbitol and threitol along with experimental data corresponding to their β_{JG} relaxations.

Several words of caution are needed when making the long extrapolation of $ln\omega_{\beta JG}$ to the A_{JG} intercept. First, $\omega_{\beta JG}$ is usually obtained over a narrow range of temperatures in the supercooled and below-T_g regions, introducing uncertainty in the slope. The data taken from the literature usually shows a slightly different slope between $ln\omega_{\alpha}$ and $ln\omega_{\beta JG}$. There may be a change in slope for $\omega_{\beta JG}$ as it passes through T_g. However, the β_{JG} data for propanol of Hansen et al. show E_a for $\beta_{JG} = 20$ kJ mol⁻¹ compared to about 24 kJ mol⁻¹ in Table 1. In contrast, the temperature dependence of the relaxation time for propanol measured by Caporaletti et al. using both BDS and nuclear resonance time-domain-interferometry, TDI, had an E_a of about 30 kJ mol⁻¹.⁵⁸ β_{JG} measured via TDI is better decoupled from the α -relaxation.⁵⁵ Whether the material is at equilibrium when β_{JG} is measured has been addressed. Wagner and Richert noted that isothermal aging of OTP, a widely studied GF, near T_g results in the loss of a peak identified as β_{JG} whereas sorbitol does not suffer from this issue.⁵⁹

In general, A_{α} for $n_{\alpha} > 1$ is often at apparently unphysical rates (e.g. $10^{16} - 10^{19}$ s⁻¹ in Table 1). Even among polymers, there is great variability in A_{α} , while ω_{Boson} for polymers is clustered around 0.5 THz.⁶⁰ Equations 13 – 15 show the role of activation entropy in TST, whatever the process, be it a unit rattle, an n_{α} rattle, or an n_{α} structural relaxation. ΔS_1^* and ΔS_{JG}^* are likely to be $<\Delta S_{struct}^*$. Qualitatively, for $n_{\alpha} > 1$, a *rearrangement* of n_{α} units involves a greater volume than a *rattle*. Since $n_{C(T)} \rightarrow 0$ at high temperature, the difference $ln\omega_{\alpha} - ln\omega_{JG} = (\Delta S_{struct}^* - \Delta S_{JG}^*)/R$. This explains the parallel nature of the $ln\omega_{\alpha}$ and extrapolated $ln\omega_{JG}$ plots at high temperature (Figure 6).

Lawson, in analyzing activated processes in solids, derived an approximate equation for relating the activation entropy to the volume change, ΔV^* , of an activated process⁶¹

$$\Delta S^* = \frac{\delta}{\theta} \Delta V^* \tag{28}$$

Where δ is the volume coefficient of thermal expansion and θ the isothermal compressibility. Polystyrene has the largest A_{α} of the polymers in Table 1, probably a result of the inherent stiffness (long persistence length) of the backbone. From Eq. 15, $lnA_{\alpha} - lnA_{0} = \Delta S^{*}_{struct}/R$. For polystyrene, using values of 6.1 x 10⁻⁴ K⁻¹ and 12.1 x 10⁻¹⁰ Pa⁻¹ at 300 °C (well into the Arrhenius regime) for δ and θ , respectively,⁶² and A₀ = 2.7 x 10¹² s⁻¹,⁶³ ΔS^*_{struct} is 117 J mol⁻¹ K⁻¹ and ΔV^* is 230 cm³ which is 2.2 molar volumes of styrene repeat units, or about one styrene from each of the n_α = 2 units rearranging in the Arrhenius region. Assuming this is the minimum free volume needed to rearrange, supplied at T_g by n_{Tg} = 13 units of persistence length 4 styrene units each, the fractional free volume, v_f, at T_g, is about 2.2/(13 x 4) = 4 %. Depending on the model, estimates of v_f for polystyrene at T_g range from about 2.5 % (Doolittle model^{7,36-37}) to 11 % (White and Lipson using a PVT model³⁴) to 12 % (from positron lifetime spectroscopy⁶⁴). Eyring's theory is also used to described plastic deformation in glasses.^{17 65} Long et al.⁶⁵ modified classical TST theory to account for a mismatch between apparent activation volumes between the linear and plastic flow regimes. In their analysis, elastic energy stored over a length scale of dynamic heterogeneities lowers the energy barrier for α-relaxation.

Relaxation plots in GFs are known to exhibit a thermodynamic scaling^{8,9} between density, ρ (controlled by pressure), and temperature: $\omega_{\alpha} \sim T/\rho^{\gamma}$. In select cases, for small van der Waals GFs such as OTP and PC, the entire relaxation spectrum in BDS follows this scaling.⁸ Such isochronal superposition (IS) could only occur if $e^{\Delta S_{struct}^*} \approx e^{\Delta S_{JG}^*}$ i.e. the activation volumes of β_{JG} and ω_{α} are similar (according to Equation 28). In addition, the ω_{α} broad band spectra at different temperatures superimpose with frequency shifting (time-temperature superposition), e.g. for OTP.⁶⁶ These small, van der Waals GFs are likely to have $n_{\alpha} = 1$. Niss and Hecksher⁶⁶ point out that polymers ironically do not show TTS over the entire BDS response. This is because n_{α} for polymers = 2.

Classes of glasses. Classification of glasses is typically done by comparing the extent to which their dynamics deviate from high-temperature Arrhenius using a steepness index or kinetic fragility, *m*, at T_g^{28}

$$m = -\left| d\log_{10} \omega_{\alpha} / d(T_g/T) \right|_{T = T_g}$$
^[29]

Using Eqs. 16 and 19, the fragility and n_{α} are related by

$$m = \frac{n_{T_g} E_a}{2.3 n_\alpha R T_g} = \frac{n_{T_g} E_1}{2.3 R T_g}$$
[30]

which provides a quick estimate of the n_{α} class using literature T_g , *m* and E_a without fitting the data over all temperatures. The origin of fragility is a perplexing issue in glass physics. From Equation 30, the origin of fragility and the reasons for the wide range of values of *m* are clear: it is a combination of three parameters. n_{Tg} has a lower spread of values (about a factor of two) than does T_g or E_1 . Some of the glass formers with a large E_a actually have much lower E_1 if n_{α} is 4. Thus, the silicate glasses, with $n_{\alpha} = 4$ and high T_gs, push fragility lower. Small molecules with low T_g and van der Waals interactions (where $n_{\alpha} = 1$) tend toward the upper half of fragilities.

Table 1 shows reasonable agreement between n_{Tg} (n at $T = T_g$) estimated with Equation 30 using the literature *m* values and those calculated using Equation 19. The actual T_g is not predicted from the equations herein, although it can be predicted with the locally correlated lattice (LCL)²¹ model, which is a first-principles thermodynamic treatment of PVT data. The LCL model frees itself of the constraint arbitrarily placed on Doolittle's free volume to make it follow VFT response.²¹

Supercooled liquids approach icosahedral ordering⁶⁷ near Tg and atomistic models show such ordering improves with observation time. 68 In fact, the CRR is only compact at $T_{\rm g}$ and, if quasiicosahedral, would imply n_{Tg} of about 13, representing a central unit surrounded by 12 nearest neighbors. The configuron percolation model⁶⁹ supports conclusions by Wendt and Abraham⁷⁰ that packing saturation of the first shell by nearest neighbors at Tg is predicted by analysis of the pair distribution function (PDF). Example X-ray scattering studies on PDFs of metallic glasses show a coordination number of about 12.3⁷¹ and 12.6⁷² From Table 1, many n_{Tg} are clustered at around 13 but this is not universal, probably reflecting anisotropy⁷³ in the interaction environment of a unit, such as the hydrogen bonding patterns in xylitol and glycerol. Note that polymers are structurally anisotropic (they are chains) but each moving unit might experience the same interaction environment.⁴² n_{Tg} is sensitive to the slope of the fit at Tg, which is least satisfactory for the OTP fit. The measured slope from the OTP data near T_g (see Figure S2) gives $n_{Tg} = 13$. Overall, the answer to "what happens at T_g ?" is, for many systems, "that is the lowest temperature where 13 neighboring units with a near-icosahedral interaction environment can cooperatively rearrange within τ_1 to provide the free volume that allows n_{α} units to rearrange simultaneously." n_{Tg} may be larger or smaller if the environment does not have icosahedral symmetry, or the units themselves adopt different ordering as required, for example, by hydrogen bonding. Dynamic modeling that starts with spherically symmetric units (e.g. beads) would be expected to achieve idealized short-range ordering approaching close packing.

If cooperativity in the first coordination shell is "saturated" at T_g , what happens when the glass is further cooled? The next-nearest neighbor shell must participate. Modeling of amorphous materials by Mercier and Levy⁷⁴ suggests that the packing goes from 13 units to 43 if the next coordination shell is included (for spherical units). One can expect another glass transition at a lower temperature where the entire shell of next-nearest neighbors must also cooperatively rearrange. The changes between coordination shells probably underly second-order like transitions such as a change in expansion coefficient and a step in heat capacity at T_g . Equation 27 is not extended below T_g as there is no basis to assume E_a remains constant below T_g . In particular, the activation energy term in Equation 15 may change. There is evidence that below T_g the relaxation response is Arrhenius with a much higher E_a than that above T_g .⁷⁵ The physical size of n_{Tg} units is reasonably consistent with experiment. For example if the actual "unit" in polystyrene is a persistence length of 1 nm which is 1/0.25 = 4 styrene repeat units and there are 13 of these at T_g, the mass of the CRR is 4 x 13 x 104 g mol⁻¹/6.02 x 10^{23} mol⁻¹ = 9.0 x 10^{-21} g or 9.0 x 10^{-20} cm³ assuming a density of 1 g cm⁻³ for a size of 2.1 nm, compared to 3.0 nm estimated by Hempel et al.⁷⁶

Shift Factors. Equation 27 can be rearranged into classical shift factors using the parameters E_a , T_{SA} and n_{α} (Section S4). In the broadly-used concept of time-temperature superposition, TTS, a shift factor a_T is employed to shift dynamic responses taken at different temperatures and is the ratio between their frequencies, $\frac{\omega_{T_1}}{\omega_{T_2}}$. A typical expression for shift factors in polymers is that of Williams, Landel and Ferry (WLF):

$$\log(a_T) = \frac{-c_1(T_1 - T_2)}{c_2 + T_1 - T_2}$$
[31]

where c_1 and c_2 are two empirical (freely adjustable) fit constants.⁷⁷ Using the appropriate substitutions (Section S4) and Equation 16, we obtain the following:

$$\ln a_T = \frac{E_a}{R} \left(\frac{1}{T_2} - \frac{1}{T_1} \right) + e^{\frac{-C}{T_{SA}}} \left(e^{\frac{C}{T_2}} - e^{\frac{C}{T_1}} \right)$$
[32]

where $C = E_a/n_a R$. This relationship shows there are two components to the shift factor; the first term on the right represents the Arrhenius response for n_a units. The second term includes the probability factor when $n_T > n_a$. The shift factor can then be written as: $a_T = a_A \times a_P$ where a_A is due to the Arrhenius shift of n_a units and a_P is due to the probability factor $e^{-n_{c(T)}}$ for additional $n_{c(T)}$ units imposed by limited free volume. Figure 7 compares shift factors obtained using the WLF equation and Equation 32 for poly(isobutyl methacrylate).



Figure 7. Example of shift factor calculations. The shift factor a_T for poly(isobutyl methacrylate) calculated using WLF Equation 31 (red circles) and Equation 32 (blue squares). The empirical WLF fit constants were: $c_1 = 12.4$ and $c_2 = 57$ °C and $T_2 = T_g$. Values for n_{α} , E_a and T_{SA} used for Equation 32 are given in Table 1.

Crossover Temperatures. While the WLF equation is mathematically equivalent to the VFT equation, it cannot be superimposed on Equations 27 or 32. The WLF and VFT equations are often unable to fit *both* the near-T_g *and* the Arrhenius regions. Equation 27, in contrast, can describe the relaxation across wide ranges of temperatures. Equation 27 handily avoids the controversy of a temperature at which ω_{α} would diverge (the Vogel temperature, T₀, section S4), close to the temperature T_K at which the entropy of a glass would be equal to the entropy of its crystalline state.⁷⁸ This divergence is also avoided by many other descriptions of glass relaxation which use characteristic temperatures greater than T_g¹. Such "crossover" temperatures define the point of departure from Arrhenius into supercooled behavior, much like T_{SA}. Stickel et al. presented way to emphasize the crossover region more sharply.¹⁵ The resulting "Stickel temperature," T_B, is in the vicinity of T_{SA} (e.g. T_B = 243 K for PPG¹²) or not very close (e.g. T_B = 296 K for OTP¹²). Martinez-Garcia et al. compared T_B with the "critical temperature," T_c, from mode coupling theory and found T_c to be in the vicinity of T_B.¹²

Cooperative Dynamics in Ion-Polymer Coupled Systems. Many phenomena are coupled to structural dynamics.⁷⁹⁻⁸⁰ For example, ion conductivity in polymers is usually shown to be coupled to the dynamics of the polymer host.⁸¹⁻⁸² The dependence of conductivity on temperature for an example ion conducting polymer is modeled well by adapting Equation 27 using $n_{\alpha} = 2$ (Figure 8 and Supplemental Information Section S5).

$$\ln \sigma_T T = \ln \sigma_{T,Arr} T - exp\left(\frac{E_a}{2R}\left(\frac{1}{T} - \frac{1}{T_{SA}}\right)\right)$$
[33]

We calculated n_{Tg} to be 13. For a particular set of variables in Eq. 33, anything that increases the activation entropy will increase σ .



Figure 8. Conductivity plot of bis(trifluoromethylsulfonyl)imide,⁸³ TF₂N⁻, in a single-ion polyviologen conductor (PV_C₆/C₁₀, structure given in inset). Solid line is Equation 33 using $n_{\alpha} = 2$, measured $E_a = 75.2$ kJ mol⁻¹, measured $T_{SA} = 317$ K.

This system is a single ion conductor, where the TF_2N^- counterion is free to transport charge through the bulk of the material, whereas the positive charge resides on the polymer chain and is thus not free to diffuse.⁸³ The conductivity σT is proportional to the ion diffusion coefficient, D_T . The good agreement given in Figure 8 supports the idea that the transport of ions is coupled to the dynamics of the host polymer. Some ion transport below T_g is claimed to be decoupled from polymer dynamics.⁸⁴ This may be true for the α -relaxation but there must still be some phonon-type of contribution from the matrix in which the ion is embedded. The "unphysically high prefactors" up to 10^{28} s⁻¹ for ion transport in polymer electrolytes recently highlighted by Gainaru et al.⁸⁴ must include a significant ΔS^* .

Cooperative Dynamics in Spin Systems. Most of the temperature-controlled glass relaxation in the literature is fit to some reasonable extent by Equation 27. The fidelity of the data is somewhat degraded on transcribing literature plots and a few degrees of error in the temperature measurement near T_{SA} would cause noticeable deviation (for an example see Figure S5B, Supplemental Information). Equation 27 broadly describes a "quenched" state where increasing numbers of cooperatively interacting units are obtained at lower temperatures with the emergence of heterogenous dynamic length scales. Spin glasses and ferromagnetic relaxors potentially fit this description. For example, Figure 9 shows

relaxation dynamics for perovskite ferroelectrics PLZT ($Pb_{1-x}La_x(Zr_{1-y},Ti_y)_{1-x/4}O_3$) and PMN-PT⁸⁵ ($Pb(Mg_{1/3}Nb_{2/3})O_3$)-PbTiO₃ represented by Equation 27 with respective n_{α} values of 0.5 and 2.



Figure 9. The frequency of ferroelectric relaxors versus 1/T. Pb(Mg_{1/3}Nb_{2/3})O₃ – PbTiO₃ (PMN-PT, \circ): $n_{\alpha} = 2$, experimental $E_a = 229$ kJ mol⁻¹, measured $T_{SA} = 319$ K; and Pb_(1-x)La_x(Zr_{1-y}Ti_y)_{1-x/4}O₃ (PLZT, \diamond): $n_{\alpha} = 0.5$, experimental $E_a = 422$ kJ mol⁻¹, measured $T_{SA} = 369$ K. Points are experimental data from ref ⁸⁵; solid line from Equation 27.

In the case of electric (or magnetic) dipoles we interpret an n_{α} of 0.5 to represent one dipole switching direction from +1 to -1 (rather than +1 to 0).

Conclusions

We have presented an equation based on measurable parameters that allows quantitative description and classification of glassy dynamics according to the minimum number of units that must rearrange simultaneously. The motion of units has been broken down into those occurring simultaneously (concerted/correlated) and those occurring within interval τ_1 . n_{α} represents the minimum cluster size of rearranging units, observed at high temperatures. These units escape their cages simultaneously with frequency ω_{α} , but only if there is enough free volume to do so. Otherwise, one observes a correlated rattle at ω_{JG} , the JG β -relaxation. ω_{JG} accounts for the Arrhenius slope of ω_{α} at high temperature. Additional spatiotemporal restrictions are encountered as the temperature drops, limiting the free volume. A probability term incorporates dynamic heterogeneity and deviation from Arrhenius due to a growing length scale of cooperativity as the glass cools.

The only freely-adjustable fitting term is n_{α} , which is an integer between 1 and 4. A mixture of kinetics and thermodynamics is inherent to Equation 12. The E_a term refers to the steady-state (equilibrium) Boltzmann distribution of the number of n_{α} units with energy sufficient to simultaneously escape their cages. The $n_{c(T)}$ term is a result of additional kinetic restrictions. Though our approach can be classified as a free volume argument, the actual free volume is not needed. Neither the free volume

at T_g , nor T_g itself is specified unless n_{Tg} is estimated for a class of materials, such as polymers, for Equation 30. In fact, the most important temperature regime is around T_{SA} because it provides E_a and T_{SA} . With the Arrhenius slope, T_{SA} , and n_{α} , the entire supercooled regime between T_{SA} and T_g is predicted with reasonable accuracy.

The results are entirely consistent with work attributing certain β -relaxations to caged precursors,^{8, 34, 86} which are unleashed above T_g as groups of n_a units assisted by cooperative motions among n_a + n_{c(T)} units. Extrapolations of ω_{α} to the liquid state (i.e. T > T_{SA}) provide deep implications on how liquids flow. For example, substances with n_a > 2 move in clusters of n_a, not as individual units. Knowing n_a should improve molecular simulations and vice versa. The persistence length exchange mechanism suggested for polymers (Figure 3), if it holds up under scrutiny from molecular dynamics simulations, may be universal for polymers. The n_a = 2 found for ionic liquids may also be universal, and may represent the place exchange of two neighboring like-charged ions to preserve the local electrostatic field.

While Equation 27 brings much-needed simplicity⁶⁶ to a quantitative relationship for glassy dynamics *versus* temperature, many challenges remain, including developing a more sophisticated picture of both the nature of a "unit", which is not necessarily spherical, and its interaction environment.

Some assumptions have been made which are not strictly valid. For example, whatever high frequency mode actually represents A_1 shows slight temperature dependence.⁵⁶ The activation barrier E_1 is also likely not constant over the supercooled region, though there may be some fortuitous cancelling of effects. A changing E_1 translates to a nonlinear Arrhenius response, which is more likely to occur with dynamics that are studied over a wide temperature range, such as those of OTP.

Author Information

Corresponding Author

J.B. Schlenoff - Department of Chemistry and Biochemistry, The Florida State University, Tallahassee, Florida 32306-4390, United States. Email: <u>jschlenoff@fsu.edu</u>

Authors

K. Akkaoui - Department of Chemistry and Biochemistry, The Florida State University, Tallahassee, Florida 32306-4390, United States

Acknowledgments

This work was supported by the National Science Foundation (grants DMR-1809304 and DMR-2103703).

Conflict of Interest

The authors have no conflicts to disclose.

Supplementary Information

Relaxations diagrams for three alcohols; individual relaxation plots of the glass formers transcribed from the literature, alongside E_a , A_α and T_{SA} ; detailed derivation of Equation 27; comparison with VFT and WLF equations; Equation 27 adapted for ionic conductivity.

References

1. Kivelson, S. A.; Tarjus, G., In Search of a Theory of Supercooled Liquids. *Nature Materials* **2008**, *7*, 831-833.

2. Debenedetti, P. G.; Stillinger, F. H., Supercooled Liquids and the Glass Transition. *Nature* **2001**, *410*, 259-267.

3. Berthier, L.; Biroli, G.; Bouchaud, J.-P.; Cipelletti, L.; Masri, D. E.; L'Hôte, D.; Ladieu, F.; Pierno, M., Direct Experimental Evidence of a Growing Length Scale Accompanying the Glass Transition. *Science* **2005**, *310*, 1797-1800.

4. Janssen, L. M. C., Mode-Coupling Theory of the Glass Transition: A Primer. *Frontiers in Physics* **2018**, *6*.

5. Málek, J., Structural Relaxation Rate and Aging in Amorphous Solids. *The Journal of Physical Chemistry C* **2023**, *127*, 6080-6087.

6. Solunov, H., On Measuring the Characteristic Length of the Cooperative Molecular Dynamics in the Glass-Forming Liquids. *J. Phys.: Conf. Ser.* **2019**, *1186*, 012008.

7. Pazmiño Betancourt, B. A.; Hanakata, P. Z.; Starr, F. W.; Douglas, J. F., Quantitative Relations between Cooperative Motion, Emergent Elasticity, and Free Volume in Model Glass-Forming Polymer Materials. *Proceedings of the National Academy of Sciences* **2015**, *112*, 2966-2971.

8. Ngai, K.; Habasaki, J.; Prevosto, D.; Capaccioli, S.; Paluch, M., Thermodynamic Scaling of α -Relaxation Time and Viscosity Stems from the Johari-Goldstein β -Relaxation or the Primitive Relaxation of the Coupling Model. *The Journal of Chemical Physics* **2012**, *137*, 034511.

9. Ngai, K. L.; Paluch, M., Classification of Secondary Relaxation in Glass-Formers Based on Dynamic Properties. *The Journal of Chemical Physics* **2004**, *120*, 857-873.

10. Tanaka, H.; Kawasaki, T.; Shintani, H.; Watanabe, K., Critical-Like Behaviour of Glass-Forming Liquids. *Nature Materials* **2010**, *9*, 324-331.

11. Hecksher, T.; Nielsen, A. I.; Olsen, N. B.; Dyre, J. C., Little Evidence for Dynamic Divergences in Ultraviscous Molecular Liquids. *Nature Physics* **2008**, *4*, 737-741.

12. Martinez Garcia, J. C.; Tamarit, J. L.; Rzoska, S. J., Enthalpy Space Analysis of the Evolution of the Primary Relaxation Time in Ultraslowing Systems. *The Journal of Chemical Physics* **2011**, *134*, 024512

13. Martinez-Garcia, J. C.; Martinez-Garcia, J.; Rzoska, S. J.; Hulliger, J., The New Insight into Dynamic Crossover in Glass Forming Liquids from the Apparent Enthalpy Analysis. *The Journal of Chemical Physics* **2012**, *137*, 064501.

14. Gao, Q.; Jian, Z., Fragility and Vogel-Fulcher-Tammann Parameters near Glass Transition Temperature. *Mater Chem Phys* **2020**, *252*, 123252.

15. Stickel, F.; Fischer, E. W.; Richert, R., Dynamics of Glass-Forming Liquids. II. Detailed Comparison of Dielectric Relaxation, DC-Conductivity, and Viscosity Data. *The Journal of Chemical Physics* **1996**, *104*, 2043-2055.

16. Novikov, V. N.; Sokolov, A. P., Temperature Dependence of Structural Relaxation in Glass-Forming Liquids and Polymers. *Entropy* **2022**, *24*, 1101.

17. Eyring, H., Viscosity, Plasticity, and Diffusion as Examples of Absolute Reaction Rates. *The Journal of Chemical Physics* **1936**, *4*, 283-291.

18. Avramov, I.; Milchev, A., Effect of Disorder on Diffusion and Viscosity in Condensed Systems. *Journal of Non-Crystalline Solids* **1988**, *104*, 253-260.

19. Hrma, P.; Ferkl, P.; Kruger, A. A., Arrhenian to Non-Arrhenian Crossover in Glass Melt Viscosity. *Journal of Non-Crystalline Solids* **2023**, *619*, 122556.

20. Macedo, P. B.; Litovitz, T. A., On the Relative Roles of Free Volume and Activation Energy in the Viscosity of Liquids. *The Journal of Chemical Physics* **2004**, *42*, 245-256.

21. Cohen, M. H.; Turnbull, D., Molecular Transport in Liquids and Glasses. *The Journal of Chemical Physics* **2004**, *31*, 1164-1169.

22. Mauro, J. C.; Yue, Y.; Ellison, A. J.; Gupta, P. K.; Allan, D. C., Viscosity of Glass-Forming Liquids. *Proceedings of the National Academy of Sciences* **2009**, *106*, 19780-19784.

23. Waterton, S., The Viscosity-Temperature Relationship and Some Inferences on the Nature of Molten and of Plastic Glass. *J. Soc. Glass Technol* **1932**, *16*, 244-247.

24. Adam, G.; Gibbs, J. H., On the Temperature Dependence of Cooperative Relaxation Properties in Glass-Forming Liquids. *The Journal of Chemical Physics* **1965**, *43*, 139-146.

25. Johari, G. P., A Resolution for the Enigma of a Liquid's Configurational Entropy-Molecular Kinetics Relation. *The Journal of Chemical Physics* **2000**, *112*, 8958-8969.

26. Berthier, L.; Ozawa, M.; Scalliet, C., Configurational Entropy of Glass-Forming Liquids. *The Journal of Chemical Physics* **2019**, *150*, 160902.

27. Tatsumi, S.; Aso, S.; Yamamuro, O., Thermodynamic Study of Simple Molecular Glasses: Universal Features in Their Heat Capacity and the Size of the Cooperatively Rearranging Regions. *Physical Review Letters* **2012**, *109*, 045701.

28. Böhmer, R.; Ngai, K.; Angell, C. A.; Plazek, D., Nonexponential Relaxations in Strong and Fragile Glass Formers. *The Journal of Chemical Physics* **1993**, *99*, 4201-4209.

29. Greet, R.; Turnbull, D., Glass Transition in O-Terphenyl. *The Journal of Chemical Physics* **1967**, *46*, 1243-1251.

30. Hung, J.-H.; Patra, T. K.; Meenakshisundaram, V.; Mangalara, J. H.; Simmons, D. S., Universal Localization Transition Accompanying Glass Formation: Insights from Efficient Molecular Dynamics Simulations of Diverse Supercooled Liquids. *Soft Matter* **2019**, *15*, 1223-1242.

31. Ediger, M. D.; Gruebele, M.; Lubchenko, V.; Wolynes, P. G., Glass Dynamics Deep in the Energy Landscape. *The Journal of Physical Chemistry B* **2021**, *125*, 9052-9068.

32. Johari, G. P., Intrinsic Mobility of Molecular Glasses. *The Journal of Chemical Physics* **1973**, 58, 1766-1770.

33. Johari, G. P.; Goldstein, M., Viscous Liquids and the Glass Transition. II. Secondary Relaxations in Glasses of Rigid Molecules. *The Journal of Chemical Physics* **1970**, *53*, 2372-2388.

34. Capaccioli, S.; Paluch, M.; Prevosto, D.; Wang, L.-M.; Ngai, K., Many-Body Nature of Relaxation Processes in Glass-Forming Systems. *The Journal of Physical Chemistry Letters* **2012**, *3*, 735-743.

35. Chang, C.; Zhang, H.; Zhao, R.; Li, F.; Luo, P.; Li, M.; Bai, H., Liquid-Like Atoms in Dense-Packed Solid Glasses. *Nature Materials* **2022**, *21*, 1240-1245.

36. Doolittle, A. K., Studies in Newtonian Flow. II. The Dependence of the Viscosity of Liquids on Free-Space. *Journal of Applied Physics* **1951**, *22*, 1471-1475.

37. Turnbull, D.; Cohen, M. H., Free-Volume Model of the Amorphous Phase: Glass Transition. *The Journal of Chemical Physics* **1961**, *34*, 120-125.

38. White, R. P.; Lipson, J. E. G., Polymer Free Volume and Its Connection to the Glass Transition. *Macromolecules* **2016**, *49*, 3987-4007.

39. Farnan, I.; Stebbins, J. F., High-Temperature Silicon-29 NMR Investigation of Solid and Molten Silicates. *Journal of the American Chemical Society* **1990**, *112*, 32-39.

40. Kegel, W. K.; van Blaaderen; Alfons, Direct Observation of Dynamical Heterogeneities in Colloidal Hard-Sphere Suspensions. *Science* **2000**, *287*, 290-293.

41. Xu, W.-S.; Douglas, J. F.; Sun, Z.-Y., Polymer Glass Formation: Role of Activation Free Energy, Configurational Entropy, and Collective Motion. *Macromolecules* **2021**, *54*, 3001-3033.

42. Schlenoff, J. B.; Akkaoui, K., Dissecting Dynamics near the Glass Transition Using Polyelectrolyte Complexes. *Macromolecules* **2021**, *54*, 3413-3422.

43. Zhang, M.; Chen, Y.; Dai, L.-h., Universal Scaling in the Temperature-Dependent Viscous Dynamics of Metallic Glasses. *The Journal of Physical Chemistry B* **2021**, *125*, 3419-3425.

44. Roland, C.; Casalini, R., Temperature Dependence of Local Segmental Motion in Polystyrene and Its Variation with Molecular Weight. *The Journal of Chemical Physics* **2003**, *119*, 1838-1842.

45. Schönhals, A.; Goering, H.; Schick, C., Segmental and Chain Dynamics of Polymers: From the Bulk to the Confined State. *Journal of Non-Crystalline Solids* **2002**, *305*, 140-149.

46. Döß, A.; Paluch, M.; Sillescu, H.; Hinze, G., Dynamics in Supercooled Polyalcohols: Primary and Secondary Relaxation. *The Journal of Chemical Physics* **2002**, *117*, 6582-6589.

47. Rivera, A.; Brodin, A.; Pugachev, A.; Rössler, E., Orientational and Translational Dynamics in Room Temperature Ionic Liquids. *The Journal of Chemical Physics* **2007**, *126*, 114503.

48. Takeuchi, A.; Kato, H.; Inoue, A., Vogel–Fulcher–Tammann Plot for Viscosity Scaled with Temperature Interval between Actual and Ideal Glass Transitions for Metallic Glasses in Liquid and Supercooled Liquid States. *Intermetallics* **2010**, *18*, 406-411.

49. Brand, R.; Lunkenheimer, P.; Schneider, U.; Loidl, A., Excess Wing in the Dielectric Loss of Glass-Forming Ethanol: A Relaxation Process. *Physical Review B* **2000**, *62*, 8878-8883.

50. Hansen, C.; Stickel, F.; Berger, T.; Richert, R.; Fischer, E. W., Dynamics of Glass-Forming Liquids. III. Comparing the Dielectric α-and β-Relaxation of 1-Propanol and O-Terphenyl. *The Journal of Chemical Physics* **1997**, *107*, 1086-1093.

51. Sanditov, D. S.; Ojovan, M. I., On Relaxation Nature of Glass Transition in Amorphous Materials. *Physica B: Condensed Matter* **2017**, *523*, 96-113.

52. Gulbiten, O.; Mauro, J. C.; Guo, X.; Boratav, O. N., Viscous Flow of Medieval Cathedral Glass. *Journal of the American Ceramic Society* **2018**, *101*, 5-11.

53. Laidler, K. J.; King, M. C., Development of Transition-State Theory. *The Journal of Physical Chemistry* **1983**, *87*, 2657-2664.

54. Schneider, U.; Brand, R.; Lunkenheimer, P.; Loidl, A., Excess Wing in the Dielectric Loss of Glass Formers: A Johari-Goldstein β Relaxation? *Physical Review Letters* **2000**, *84*, 5560-5563.

55. Ngai, K. L., Microscopic Understanding of the Johari-Goldstein β Relaxation Gained from Nuclear- γ Resonance Time-Domain-Interferometry Experiments. *Phys Rev E* **2021**, *104*, 015103.

González-Jiménez, M.; Barnard, T.; Russell, B. A.; Tukachev, N. V.; Javornik, U.; Hayes, L.-A.; Farrell, A. J.; Guinane, S.; Senn, H. M.; Smith, A. J.; Wilding, M.; Mali, G.; Nakano, M.; Miyazaki, Y.; McMillan, P.; Sosso, G. C.; Wynne, K., Understanding the Emergence of the Boson Peak in Molecular Glasses. *Nat Commun* 2023, *14*, 215.

57. Angell, C. A.; Yue, Y.; Wang, L.-M.; Copley, J. R.; Borick, S.; Mossa, S., Potential Energy, Relaxation, Vibrational Dynamics and the Boson Peak, of Hyperquenched Glasses. *Journal of Physics: Condensed Matter* **2003**, *15*, S1051.

58. Caporaletti, F.; Capaccioli, S.; Valenti, S.; Mikolasek, M.; Chumakov, A. I.; Monaco, G., Experimental Evidence of Mosaic Structure in Strongly Supercooled Molecular Liquids. *Nat Commun* **2021**, *12*, 1867.

59. Wagner, H.; Richert, R., Equilibrium and Non-Equilibrium Type β-Relaxations: D-Sorbitol Versus O-Terphenyl. *The Journal of Physical Chemistry B* **1999**, *103*, 4071-4077.

60. Hong, L.; Begen, B.; Kisliuk, A.; Alba-Simionesco, C.; Novikov, V. N.; Sokolov, A. P., Pressure and Density Dependence of the Boson Peak in Polymers. *Physical Review B* **2008**, *78*, 134201.

61. Lawson, A. W., Correlation of ΔS^* and ΔV^* in Simple Activated Processes in Solids. *J. Phys. Chem. Solids* **1957**, *3*, 250-252.

62. Mark, J. E., *Physical Properties of Polymers*. 3rd ed.; Cambridge University Press: Cambridge ; New York, 2004; p xv, 519 p.

63. Hong, L.; Gujrati, P. D.; Novikov, V. N.; Sokolov, A. P., Molecular Cooperativity in the Dynamics of Glass-Forming Systems: A New Insight. *The Journal of Chemical Physics* **2009**, *131*, 194511.

64. Takahashi, K. Z., Mapping Positron Annihilation Lifetime Spectroscopy Data of a Polymer to Classical Molecular Dynamics Simulations without Shifting the Glass Transition Temperature. *The Journal of Chemical Physics* **2023**, *159*.

65. Long, D. R.; Conca, L.; Sotta, P., Dynamics in Glassy Polymers: The Eyring Model Revisited. *Physical Review Materials* **2018**, *2*, 105601.

66. Niss, K.; Hecksher, T., Perspective: Searching for Simplicity Rather Than Universality in Glass-Forming Liquids. *The Journal of Chemical Physics* **2018**, *149*, 230901.

67. Mauro, N.; Blodgett, M.; Johnson, M.; Vogt, A.; Kelton, K., A Structural Signature of Liquid Fragility. *Nature Communications* **2014**, *5*, 1-7.

68. Hedges, L. O.; Jack, R. L.; Garrahan, J. P.; Chandler, D., Dynamic Order-Disorder in Atomistic Models of Structural Glass Formers. *Science* **2009**, *323*, 1309-1313.

69. Ojovan, M. I.; Louzguine-Luzgin, D. V., Revealing Structural Changes at Glass Transition Via Radial Distribution Functions. *The Journal of Physical Chemistry B* **2020**, *124*, 3186-3194.

70. Wendt, H. R.; Abraham, F. F., Empirical Criterion for the Glass Transition Region Based on Monte Carlo Simulations. *Physical Review Letters* **1978**, *41*, 1244-1246.

71. Tong, X.; Wang, G.; Stachurski, Z. H.; Bednarčík, J.; Mattern, N.; Zhai, Q. J.; Eckert, J., Structural Evolution and Strength Change of a Metallic Glass at Different Temperatures. *Scientific Reports* **2016**, *6*, 30876.

72. Georgarakis, K.; Louzguine-Luzgin, D. V.; Antonowicz, J.; Vaughan, G.; Yavari, A. R.; Egami, T.; Inoue, A., Variations in Atomic Structural Features of a Supercooled Pd–Ni–Cu–P Glass Forming Liquid During in Situ Vitrification. *Acta Materialia* **2011**, *59*, 708-716.

73. Tu, W.; Valenti, S.; Ngai, K. L.; Capaccioli, S.; Liu, Y. D.; Wang, L.-M., Direct Evidence of Relaxation Anisotropy Resolved by High Pressure in a Rigid and Planar Glass Former. *The Journal of Physical Chemistry Letters* **2017**, *8*, 4341-4346.

74. Mercier, D.; Levy, J.-C. S., Construction of Amorphous Structures. *Physical Review B* **1983**, 27, 1292-1302.

75. Yoon, H.; McKenna, G. B., Testing the Paradigm of an Ideal Glass Transition: Dynamics of an Ultrastable Polymeric Glass. *Science Advances* **2018**, *4*, eaau5423.

76. Hempel, E.; Hempel, G.; Hensel, A.; Schick, C.; Donth, E., Characteristic Length of Dynamic Glass Transition near T_g for a Wide Assortment of Glass-Forming Substances. *Journal of Physical Chemistry B* **2000**, *104*, 2460-2466.

77. Williams, M. L.; Landel, R. F.; Ferry, J. D., The Temperature Dependence of Relaxation Mechanisms in Amorphous Polymers and Other Glass-Forming Liquids. *Journal of the American Chemical society* **1955**, *77*, 3701-3707.

78. Kauzmann, W., The Nature of the Glassy State and the Behavior of Liquids at Low Temperatures. *Chemical Reviews* **1948**, *43*, 219-256.

79. Ngai, K., L., Structural Relaxation and Conductivity Relaxation in Glassy Ionics. *J. Phys. IV* **1992**, *02*, C2-61-C2-73.

80. Lundin, F.; Idström, A.; Falus, P.; Evenäs, L.; Xiong, S.; Matic, A., Ion Dynamics and Nanostructures of Diluted Ionic Liquid Electrolytes. *The Journal of Physical Chemistry C* **2022**, *126*, 16262-16271.

81. Mongcopa, K. I. S.; Tyagi, M.; Mailoa, J. P.; Samsonidze, G.; Kozinsky, B.; Mullin, S. A.; Gribble, D. A.; Watanabe, H.; Balsara, N. P., Relationship between Segmental Dynamics Measured by Quasi-Elastic Neutron Scattering and Conductivity in Polymer Electrolytes. *ACS Macro Letters* **2018**, *7*, 504-508.

82. Doi, Y.; Allgaier, J.; Zorn, R.; Förster, S.; Egami, T.; Ohl, M., Relaxation Dynamics and Ion Conduction of Poly(Ethylene Carbonate/Ethylene Oxide) Copolymer-Based Electrolytes. *The Journal of Physical Chemistry C* **2022**, *126*, 20284-20292.

83. Lee, M.; Gibson, H. W.; Kim, T.; Colby, R. H.; Choi, U. H., Ion–Dipole-Interaction-Driven Complexation of Polyethers with Polyviologen-Based Single-Ion Conductors. *Macromolecules* **2019**, *52*, 4240-4250.

84. Gainaru, C.; Kumar, R.; Popov, I.; Rahman, M. A.; Lehmann, M.; Stacy, E.; Bocharova, V.; Sumpter, B. G.; Saito, T.; Schweizer, K. S.; Sokolov, A. P., Mechanisms Controlling the Energy Barrier for Ion Hopping in Polymer Electrolytes. *Macromolecules* **2023**, *56*, 6051-6059.

85. Levit, R.; Martinez-Garcia, J. C.; Ochoa, D. A.; García, J. E., The Generalized Vogel-Fulcher-Tamman Equation for Describing the Dynamics of Relaxor Ferroelectrics. *Scientific Reports* **2019**, *9*, 12390.

86. Ngai, K.; Fytas, G., Why the Relaxation Times of Polymers from Brillouin Light Spectroscopy Are Much Shorter Than the Primary α-Relaxation Times. *Macromolecules* **2019**, *52*, 8305-8311.

Supplemental Information



Figure S1. Relaxations in two alcohols: **A**, sorbitol; **B**, threitol. Rates ω_{α} and $\omega_{\beta JG}$ and ω_{1} . β_{JG} relaxation (s⁻¹) for sorbitol (n_{α} = 2) and threitol (n_{α} = 3) as a function of 1/T (dashed line). ω_{1} (slope = E₁/R). Respective $A_{\alpha} = 1 \ge 10^{18} \text{ s}^{-1}$ and 6.3 $\ge 10^{16} \text{ s}^{-1}$; E_a = 60.5 kJ mol⁻¹ and 44.8 kJ mol⁻¹. T_{SA} = 340 and 342 K for sorbitol and threitol, respectively. A₁ = 8.8 $\ge 10^{12} \text{ and } 5.8 \ge 10^{12} \text{.}^{88-89}$ The β_{JG} relaxations are from reference 46: A_{JG} = 7.7 $\ge 10^{16} \text{ s}^{-1}$ and 7.9 $\ge 10^{12} \text{ s}^{-1}$, E_{a,JG} = 61 kJ mol⁻¹ and 43 kJ mol⁻¹.

Section S1: Probability for unit move

A Poisson distribution describes the probability that a given number of random events will occur in a fixed interval of time, and is given by a probability mass function, p(k), with k the number of occurrences: $p(k) = \frac{\lambda^k}{k!}e^{-\lambda}$. The probability, p(k = 1), of a specific unit (k = 1) moving in its cage in τ_1 seconds, with an average rate $\lambda = 1$ move per τ_1 seconds, is $p(k) = \frac{1^1}{1!} \left(\frac{1}{e}\right)$.

Section S2: Free volume

The purpose of $n_{c(T)}$ unit movement is to concentrate free volume around n_{α} units. One can estimate the outcome of this for polymers ($n_{\alpha} = 2$). Suppose the minimum local fractional free volume required for 2 units to slide past each other (see Figure 4D) is $v_{f\alpha}$. If the average free volume of a unit at a particular temperature is $v_{f1(T)}$, the total localized free volume is $n_T v_{f1(T)}$. For polymers, above T_{SA} , $2v_{f1(T)} > v_{f\alpha}$. Below T_{SA} , $2v_{f1(T)} < v_{f\alpha}$, so $n_{c(T)}$ units must contribute additional free volume.

Section S3:

Equation 22 is reproduced here.

$$\frac{d\ln\omega_{\alpha}}{dT^{-1}} - \frac{E_1}{R}\ln\omega_{\alpha} + \frac{E_1}{R}\left(n_{\alpha} + \ln A_{\alpha} - \frac{n_{\alpha}E_1}{RT}\right) = 0$$
[S1]

Equation S1 is a first order non homogenous differential equation of the form: y' +ay +bx +c =0 where $y = \ln \omega_{\alpha}$, $x = T^{-1}$ and $a = -\frac{E_1}{R}$, $b = -\frac{n_{\alpha}E_1^2}{R^2}$, $c = \frac{E_1}{R}(n_{\alpha} + \ln A_{\alpha})$. The solution is given by $y = \frac{b}{a^2} - \frac{b}{a}x - \frac{c}{a} + c_1e^{\frac{E_1}{RT}}$







Figure S2. Relaxation in glass-forming liquids. The structural relaxation rate in 16 glasses given by experimental data transcribed from the literature (open circles), comparison to Equation 27 (blue curve) using the parameters given in Table 1, and the Arrhenius frequency (red line). Insets show the n_{α} class and the structure (when applicable).







Figure S3. Estimating E_a and A_α from high T data. Relaxation frequencies, ω_α (s⁻¹) given in the Arrhenius region (T > T_{SA}) for the glass formers analyzed *versus* 1/T. The blue circles are data transcribed from the literature. Blue dotted line is a linear fit of *ln* frequency *vs.* 1/T (fit equation shown). The molar activation energies, E_a , are calculated by multiplying slopes by the gas constant (R = 8.314 J K⁻¹ mol⁻¹). The intercept gives the preexponential factor $ln A_\alpha$.









Figure S4. Locating T_{SA} . Plots of $\ln(\omega_{\alpha,arr}/\omega_{\alpha})$ as a function of temperature allow the estimation of T_{SA} using experimental data (at T_{SA} , $\ln(\omega_{\alpha,arr}/\omega_{\alpha}) = 1.0$). The circles are experimental data within an appropriate range for T_{SA} estimation. The dashed lines are guides to the eye.



Figure S5. (**A**) Varying n_{α} . Varying n_{α} in poly(vinylacetate) ($n_{\alpha} = 2$). The circles are experimental data taken from the literature (see Table 1 for the reference). The solid curve is the fit for $n_{\alpha} = 2$. The red short-dashed curve is the fit using $n_{\alpha} = 3$ and the blue long-dash curve is the fit using $n_{\alpha} = 1$. (**B**) Varying T_{SA} . The solid blue curve uses $T_{SA} = 290$ K as read from Figure S4. Red short-dash curve is $T_{SA} = 305$ K. Blue long-dash curve is $T_{SA} = 275$ K.

Section S4: Shift factor *a_T*

The Williams-Landel-Ferry (WLF) equation defines a shift factor, a_T , used for timetemperature superposition, usually on polymers. It gives a ratio of the rate, $\omega_{\alpha,T}$ at two different temperatures T_1 and T_2

$$a_T = \frac{\omega_{\alpha, T_1}}{\omega_{\alpha, T_2}}$$
[S2]

One temperature is usually selected as a reference (often T_g). The WLF equation gives an empirical relationship between a_T , T_1 and T_2 and two empirical fit constants c_1 and c_2 adjusted to fit the data

$$\log(a_T) = \frac{-c_1(T_1 - T_2)}{c_2 + T_1 - T_2}$$
[S3]

The mathematically equivalent VFT equation usually fits relaxation response in the range of temperature T_g to about $T_g + 100$ K

$$\omega_{T,VFT} = \omega_{0,VFT} e^{\frac{-DT_o}{T-T_o}}$$
[S4]

Where $\omega_{0,VFT}$, D and T_o are empirical fit parameters. T_o is known as the Vogel temperature and is usually about 50 K below T_g. The equivalent form for viscosity, η , is

$$\eta_{T,VFT} = \eta_{o,VFT} e^{\frac{DT_o}{T-T_o}}$$
[S5]

Combining Equations 27 and S2 gives a form of the shift factor between T_1 and T_2 using E_a , T_{SA} , and n_{α} .

$$\ln a_T = \frac{E_a}{R} \left(\frac{1}{T_2} - \frac{1}{T_1} \right) + e^{\frac{-E_a}{n_a R T_{SA}}} \left(e^{\frac{E_a}{n_a R T_2}} - e^{\frac{E_a}{n_a R T_1}} \right)$$
[S6]

The WLF equation does not map directly onto Equation S6 but a new constant *c* may be defined as follows

$$c = \frac{E_a}{n_a R}$$
[S7]

Therefore,

$$\ln a_T = \frac{E_a}{R} \left(\frac{1}{T_1} - \frac{1}{T_2} \right) - e^{-\frac{C}{T_{SA}}} \left(e^{\frac{C}{T_2}} - e^{\frac{C}{T_1}} \right)$$
[S8]

Section S5: Diffusion and ion conductivity

Equation 27 adapted for the dependence of ion conductivity on temperature in polymers ($n_{\alpha} = 2$) reads

$$\ln D_T = \ln D_{Arr} - exp\left(\frac{E_a}{2R}\left(\frac{1}{T} - \frac{1}{T_{SA}}\right)\right)$$
[S9]

It follows Arrhenius behavior at sufficiently high temperatures

$$D_{T,Arr} = D_0 e^{-E_a/RT}$$
 [S10]

The Nernst-Einstein equation relates conductivity σ_T to D_T in a single-ion conductor:

$$\sigma_T = \frac{q^2 C D_T N_A}{k_B T}$$
[S11]

where N_A is Avogadro's number, *C* is the ion concentration (moles m⁻³), k_B is Boltzmann's constant and *q* is the charge of the ion. The conductivity would read

$$\ln \sigma_T T = \ln \sigma_{T,Arr} T - exp\left(\frac{E_a}{2R}\left(\frac{1}{T} - \frac{1}{T_{SA}}\right)\right).$$
 [S12]

For $T > T_{SA}$, assuming *C* does not change significantly with temperature

$$\sigma_T T = A_\sigma e^{-E_a/RT}$$
[S13]

where $A_{\sigma} = \frac{q^2 C D_0 N_A}{k_B}$.